



Remediation of Pesticides using Nanomaterials : An overview

Sahithya K and Nilanjana Das*

Environmental Biotechnology Division, School of Biosciences and Technology,
VIT University, Vellore, Tamil Nadu-632014, India

Abstract: An intensive use of pesticides in agriculture has caused serious health and environmental problems. Various adsorbents and photocatalysts have been used for the remediation of pesticides from aqueous environment. In recent years, nanomaterials viz. nanocomposites and nano-biocomposites are playing a promising role towards the removal of pesticides. The present review focuses the updated information on pesticide removal using nanocomposites and nano-biocomposites through adsorption and photocatalytic degradation.

Keywords: Adsorption, nano-biocomposites, nanocomposites, photocatalytic degradation, pesticides.

1. Introduction

Leaching and persistence of chemical pesticides are the main reasons for the organic pollution in the environment¹. Industrial wastewaters are also the significant sources of the pesticide pollution in aquatic system which is a great threat to general public health due to their high toxicity. Several approaches such as oxidation, fluid-extraction, biodegradation, ozonation, chlorination, and membrane separation were reported for the removal of pesticides from aquatic environment^{2,3}. However, these techniques do not lead to the complete removal of pesticide and further treatments are needed to convert the pesticides into harmless products such as CO₂ and H₂O⁴. Hence, there is a need to develop efficient techniques which should be cost effective and eco-friendly offering high removal rates.

Adsorption has emerged as the most efficient, simple and promising fundamental technique in the waste water treatment process which certainly aims for the removal of organic pollutants⁵.

In recent years, heterogeneous photocatalysis using a semiconductor and photon energy has been emerged as a new approach for the degradation of organic pollutants. It is based on the principle that when a semiconductor is exposed to a light source of particular wavelength, the electrons from valence band are promoted to the conduction band leaving the positive holes. The generated electron-hole pairs moves to the surface of semiconductor and degrades the organic pollutants into nontoxic products^{6,7,8}.

The impacts of nanotechnology are evident in all areas including the field of environmental studies and treatments. Nanoparticles being nano-sized exhibit advanced characteristics based on their properties such as size, morphology and other size dependent properties⁹. Due to the advanced properties, nanoparticles have been employed in water treatment systems¹⁰.

With the recent developments in the field of nanotechnology, the correlation of material properties with filler size has become a point of great interest. Nanocomposites based on metallic nanoparticles have witnessed an exponential growth in the field of nanotechnology. They have also emerged as suitable alternatives to

overcome the limitations of microcomposites and monolithics. The unique properties derived from the nanocomposites can be exploited in various fields of science and technology¹¹.

In addition, biopolymers have also attracted a lot of research attention being nontoxic, low cost and eco-friendly. The physio-chemical characteristics of biopolymers favour the adsorption process in removal of various environmental pollutants. Based on the manufacturing process, biopolymers are classified into two categories viz. natural polymers and synthetic polymers. The natural polymers include polysaccharides (e.g. cellulose, chitosan, gums, alginate, agar, starch etc.) and some proteins from plant and animal origin. The synthetic polymers include polyhydroxy alkonates, poly vinyl alcohol, poly lactic acid, poly glycolic acid etc. However, the industrial performances of biopolymers are generally limited by the low thermal stability, poor mechanical and barrier properties¹². To overcome the above disadvantages associated with biopolymers, a unique approach of incorporation the nanofillers into biopolymer matrix was introduced to improve their mechanical, barrier properties and thermal stability¹³. These 'nano-biocomposites' have received increasing attention as potential adsorbents towards reducing environmental pollution which incorporates the advantages of both biopolymers and nanoparticles. This article gives a brief overview on application of nanocomposites and nano-biocomposites towards the removal of pesticides from aqueous environment.

2. Adsorbents and photocatalysts for pesticides removal

A wide range of adsorbents for the removal of various pesticides have been reported in the literature which includes agricultural waste such as rice husk¹⁴ and ground net shell¹⁵; carbonaceous materials viz., activated carbon^{16,17}; clay minerals such as zeolite^{18,19}, montmorillonite²⁰, bentonite²⁰, calcite²¹, kaolinite²¹. In addition, biopolymers viz., chitosan^{22,23} and alginate²³ were also employed in the adsorption of pesticides.

Nanomaterials including silver³, titanium dioxide²⁴, zinc oxide²⁵ were used as photocatalysts for the heterogeneous degradation of pesticides.

3. Nano-composites

Nanocomposites are prepared by reinforcing the nano sized inclusion (nanofiller) into the material which aims to improve the optical, catalytic, mechanical, magnetic, thermal, barrier and other properties. Depending on the type of nanofiller used, the nanocomposites could show the drastic modifications in their properties. Nanofillers are generally classified into three types based on their geometry and aspect ratio: Layered silicates (e.g. clays), spherical (e.g. silica) and acicular (e.g. CNT). At present, layered silicates are most widely studied due to the ease of availability, versatility and eco-friendly nature²⁶.

Based on the type of matrix used, the nano-composites are divided into three categories viz. Ceramic matrix nano-composites (e.g. Al₂O₃/SiO₃, SiO₂/Ni), Metal matrix nanocomposites (e.g. Co/Cr, Fe/MgO) and Polymer matrix nanocomposites (e.g. polyester/TiO₂). All the three categories of these nanocomposites have been exploited in field of environmental science where the applications are mainly focused on the removal of inorganic and organic pollutants from aqueous environment²⁷.

Anandan et al²⁸ reported the preparation of ZnO/clay nanocomposites of different concentrations of ZnO and three different H-form of zeolites such as Y, β and ZSM-5 that differs in Si:Al ratios and their applications towards pesticide degradation. The results showed complete degradation of monocrotophos by ZnO/Hβ at 5 % loading of ZnO. Similarly, Fe/zeolite and TiO₂/zeolite nanocomposites were reported to show the complete removal of methomyl, monocrotophos and dichlorvos through photocatalytic degradation mechanism^{29,30,31}. A polymer matrix nanocomposite was prepared by Jing et al.³² using polystyrene and Fe₃O₄ nanofillers by in-situ polymerization method to investigate the efficiency of polystyrene in removal of organochlorine pesticides through adsorption mechanism. The nanocomposites exhibited the lower uptake of aldrin, endrin and lindane pesticides in batch studies and the performance of polymer matrix nanocomposites was low when compared with other alternatives. However, they could show the better performance in removing the ng ml⁻¹ level of pesticides from contaminated water.

The applications of nanocomposites for pesticides removal are summarized in Table 1.

Table 1. Nano-composites used for the removal of pesticides

Pesticide Group	Target pesticide	NPs	Support	Mechanism of removal	Removal	Reference
Carbamate	methomyl	Fe	Zeolite	Photo catalytic oxidation	100 %	²⁹
Organo Chlorine	Aldrin	Fe ₃ O ₄	Poly styrene	Adsorption	24.7 mg g ⁻¹	³²
	Endrin	Fe ₃ O ₄	Poly styrene	Adsorption	33.5 mg g ⁻¹	³²
	Lindane	Fe ₃ O ₄	Poly styrene	Adsorption	10.2 mg g ⁻¹	³²
	Di and tri Chlorophenoxy acetic acid	ZnO/ γ -Fe ₂ O ₃	-	Photo catalytic degradation	55.2 and 57.0 %	³³
	4-Chloro phenol	C/ZnO/CdS	-	Photo catalytic degradation	98.0 %	⁸
	Lindane	Ag	Reduced graphene oxide	Degradation	99.9 %	³⁴
Organo Phosphate	Monocrotophos	TiO ₂	Zeolite	Photo catalytic degradation	100 %	³¹
		ZnO	Zeolite	Photo catalytic degradation	100 %	²⁸
	Malathion	Au/TiO ₂	-	Photo catalytic degradation	30.0 %	³⁵
	Chlorpyrifos	CoFe ₂ O ₄ @TiO ₂	Reduced graphene oxide	Photo catalytic degradation	89.9 %	³⁶
	Dichlorvos	CuO	MMT	Adsorption	83.2 %	³⁷
TiO ₂		Zeolite	Photo catalytic degradation	100 %	³¹	
Pyridazine	Chloridazon	Au/TiO ₂	-	Photo catalytic degradation	50.0 %	³⁵

4. Nano-biocomposites

Nano-biocomposites are the new class of composite materials where nanofillers are incorporated into biopolymer matrix using various techniques. The incorporation of appropriate nanoparticles into biopolymers will provide special properties which can be used for wide range of both conventional and emerging applications. The hydrophilic nature of biopolymers makes them potential adsorbents for remediation of pollutants from aqueous environment. Use of biopolymers is an innovating answer to replace the conventional and durable synthetic polymers¹³.

The three major techniques involved in the incorporation of nanofiller into the polymer matrix are (i) in-situ polymerization, (ii) solvent intercalation and (iii) melt intercalation process. In in-situ polymerization, the polymerization of monomer solution is initiated in presence of layered silicates which increases the molecular weight of layered silicates showing fully exfoliated morphology. The solvent intercalation method

involves the solvent in which the biopolymers are soluble. The biopolymer is added to an appropriate solvent followed by the nanofiller. Then, both the systems are pooled together leading to a polymer chains intercalation. This method is used to produce nano-biocomposites of polysaccharide/nanofiller and proteins/nanofiller. In melt intercalation process, both nanofiller and biopolymer are introduced simultaneously to the mixing system. This method is widely adopted due to its simplicity¹³.

Saifuddin *et al.*³⁸ demonstrated the synthesis of Ag/chitosan nano-biocomposite by melt intercalation process in which both silver nitrate solution and chitosan solution was mixed together and subjected to microwave irradiation. The reduction of silver nitrate was noticed when exposed to irradiation thereby leading to the formation of Ag nanoparticles. Thus, the synthesised Ag/chitosan nano-biocomposite showed the higher removal of atrazine pesticide in column mode. Similarly, the chitosan based nano-biocomposites were proved to show the higher removal of organophosphate pesticides^{2,39}. Preparation of nano-biocomposites using two nanofillers along with biopolymers and their applications on removal of dichlorvos has been reported recently by Sahithya *et al.*³⁷. Higher removal of dichlorvos by CuO-montmorillonite-chitosan and CuO-montmorillonite-gum ghatti nano-biocomposites suggested that biopolymers can play major role in the adsorption of pesticide. Reports are scanty on the use of nano-biocomposites on pesticide removal.

Table 2 summarizes the applications of nano-biocomposites on pesticides removal.

Table 2. Applications of nano-biocomposites for removal of pesticides

Pesticide group	Target pesticide	NPs	Biopolymer matrix	Mechanism of removal	Removal (%)	Reference
Organo phosphate	Malathion	CuO	Chitosan	Adsorption	99.9	²
	Dichlorvos	CuO-MMT	Chitosan	Adsorption	93.4	³⁷
		CuO-MMT	Gum ghatti	Adsorption	87.8	³⁷
		CuO-MMT	Poly lactic acid	Adsorption	63.3	³⁷
Pyrethroid	Permethrin	ZnO	Chitosan	Adsorption	99.0	³⁹
Triazines	Atrazine	Ag	Chitosan	Adsorption	94.0	³⁸

5. Conclusion

This review presents the applications of nano-composites and nano-biocomposites towards the removal of pesticides from aqueous environment. The reported performances of nano-composites on pesticide removal are quite encouraging. Since industries are concerned with sustainable developments, and the production cost of biopolymers is decreasing, strong developments of biopolymers-based nano-biocomposites is needed in near future. Extensive research should be carried out to promote the large scale use of nano-biocomposites for the effective removal of pesticides from wastewater.

6. Acknowledgement:

The authors are thankful to VIT University for providing necessary support throughout the study.

References:

1. Ioannidou O.A., Zabaniotou A.A., Stavropoulos G.G., Islam M.A., and Albanis T.A., Preparation of activated carbons from agricultural residues for pesticide adsorption. *Chemosphere*. 2010, 80, 1328-1336.
2. Jaiswal M., Chauhan D., and Sankararamkrishnan N., Copper chitosan nanocomposites: synthesis, characterization, and application in removal of organophosphorous pesticide from agricultural runoff. *Environ. Sci. Pollut. R.* 2012, 19, 2005-2062.
3. Manimegalai G., Shanthakumar S., and Sharma C., Silver nanoparticles: synthesis and application in mineralization of pesticides using membrane support. *Int. Nano. Lett.* 2014, 4:105, 1-5.

4. Reddy P.V.L., and Kim K.H., A review of photochemical approaches for the treatment of a wide range of pesticides, *J. Hazard. Mater.* 2015, 285, 325-335.
5. Foo K.Y., and Hameed B.H., Detoxification of pesticide waste via activated carbon adsorption process. *J. Hazard. Mater.* 2010, 175, 1-11.
6. Yasmina M., Mourad K., Mohammed S.H., and Khaoula C., Treatment heterogeneous photocatalysis; Factors influencing the photocatalytic degradation by TiO₂. *Energy. Procedia.* 2014, 50, 559-566.
7. Ahmed S., Rasul M.G., Martens W.N., Brown R., and Hashib M.A., Heterogeneous photocatalytic degradation of phenols in wastewater: A review on current status and developments. *Desalination*, 2010, 261, 3-18.
8. Lavand A.B., and Malghe Y.S., Visible light photocatalytic degradation of 4-chlorophenol using C/ZnO/CdS nanocomposites. *J. Saudi. Chem. Soc.* 2015 <http://dx.doi.org/10.1016/j.jscs.2015.07.001>.
9. Smith A.M., Duan H., Rhyner M.N., Ruan G., and Nie S.A., A systematic examination of surface coatings on the optical and chemical properties of semiconductor quantum dots. *Phys. Chem. Chem. Phys.* 2006, 8, 3895-3903.
10. Tiwari D.K., Behari J., and Sen P., Application of nanoparticles in waste water treatment. *World Appl. Sci. J.* 2008, 3, 417-433.
11. Armelao L., Barreca D., Bottaro G., Gasparotto A., Gross S., Maragno C., and Tondello E., Recent trends on nanocomposites based on Cu, Ag and Au clusters: A closer look. *Coord. Chem. Rev.* 2006, 250, 1294-1314.
12. Rhim J.W., Park H.M., and Ha C.S., Bio-nanocomposites for food packaging applications. *Prog. Polym. Sci.* 2013, 38, 1629-1652.
13. Averous L., and Pollet E., Green Nano-biocomposites. *Green. Energy. Technol.* 2012, http://dx.doi.org/10.1007/978-1-4471-4108-2_1.
14. Rojas R., Morillo J., Usero J., Vanderlinden E., and Bakouri H.E., Adsorption study of low-cost and locally available organic substance and a soil to remove pesticides from aqueous solutions. *J. Hydrol.* 2015, 520, 461-472.
15. Gimba C.E., Salihu A.A., Kagbu J.A., Turoti M., Itodo A.U., and Sariyya A.I., Study of pesticide (Dichlorvos) removal from aqueous medium by *Arachis hypogaea* (groundnut) shell using GC/MS. *World. Rural. Obs.* 2010, 2, 1-9.
16. Taha S.M., Amer M.E., Elmarsafy A.E., and Elkady M.Y., Adsorption of 15 different pesticides on untreated and phosphoric acid treated biochar and charcoal from water. *J. Environ. Chem. Eng.* 2014, 2, 2013-2025.
17. Vukcevic M.M., Kalijadis A.M., Vasiljevic T.M., Babic B.M., Lausevic Z.V., and Lausevic M.D., Production of activated carbon derived from waste hemp (*Cannabis sativa*) fibers and its performance in pesticide adsorption. *Microporous. Mesoporous. Mater.* 2015, 214, 156-165.
18. Lemic J., Kovacevic D., Canovic M.T., Kovacevic D., Stannic T., and Pfend R., Removal of atrazine, lindane and diazinone from water by organo-zeolites. *Water Res.* 2006, 40, 1079-1085.
19. Smedt C.D., Ferrer F., Leus K., and Spanoghe P., Removal of pesticides from aqueous solutions by adsorption on zeolites as solid adsorbents. *Adsorpt. Sci. Technol.* 2015, 33, 457-
20. Devies J.E.D., and Jabeen N., The adsorption of herbicide and pesticides on clay minerals and soils Part 2. Atrazine. 2003, 46, 57-64.
21. Clausen L., Fabricius I., and Madsen L., Adsorption of pesticides onto quartz, calcite, kaolinite and α -alumina. *J. Environ. Qual.* 2001, 30, 846-857.
22. Abdeen Z., and Mohammad S.G., Study of the adsorption efficiency of an eco-friendly carbohydrate polymer for contaminated aqueous solution by organophosphorous pesticides. *Open J. Org. Polym. Mater.* 2014, 4, 16-28.
23. Carnerio R.T.A., Taketa T.B., Neto R.J.G., Oliveira J.L., Campos E.V.R., Moraes M.A., Silva C.M.G., Beppu M.M., and Fraceto L.F., Removal of glyphosate herbicide from water using biopolymers membranes. *J. Environ. Manage.* 2015, 151, 353-360.
24. Carbajo J., Munoz P.G., Moranchel A.T., Faraldos M., and Bahamonde A., Effect of water composition on the photocatalytic removal of pesticides with different TiO₂ catalysts. *Environ. Sci. Pollut. R.* 2014, 21, 12233-12240.
25. Burbano J., Cruz I., Marquez J.C., Vasquez A.L., and Machuca F., Evaluation of zinc oxide based photocatalytic degradation of a commercial pesticide. *J. Adv. Oxid. Technol.* 2008, 11, 49-55.
26. Bordes P., Pollet E., and Averous L., Nano-biocomposites: Biodegradable polyester/nanoclay systems. *Prog. Polym. Sci.* 2009, 34, 125-155.

27. Camargo P.H.C., Satyanarayana K.G., and Wypych F., Nanocomposites: Synthesis, structure, properties and new application opportunities. *Mater. Resear.* 2009, 12, 1-39.
28. Anandan S., Vinu A., Venkatachalam N., Arabindoo B., Murugesan V., Photocatalytic activity of ZnO impregnated H β and mechanical mix of ZnO/H β in the degradation of monocrotophos in aqueous solution. *J. Mol. Catal.* 2006, 256, 312-320.
29. Tomasevic A., Kiss E., Petovic S., and Mijin D., Study on the photocatalytic degradation of insecticide methomyl in water. *Desalination.* 2010, 262, 228-234.
30. Shankar M.V., Cheralathan K.K., Arabindoo B., Palanichamy M., and Murugesan V., Enhanced photocatalytic activity for the destruction of monocrotophos pesticide by TiO₂/H β . *J. Mol. Catal. A: Chem.* 2004, 223, 195-200.
31. Gomez S., Marchena C.L., Renzini M.S., Pizzio L., and Pierella L., In situ generated TiO₂ over zeolitic supports as reusable photocatalysts for the degradation of dichlorvos. *Appl. Catal. B: Environ.* 2015, 162, 167-173.
32. Jing L., Yang C., and Zongshan Z., Effective organochlorine pesticides removal from aqueous systems by magnetic nanospheres coated with polystyrene. *J. Wuhan. University. Technol.* 2013, 29, 168-173.
33. Abdullah A.H., Mun L.K., Zainal Z., and Hussein M.Z., Photodegradation of chlorophenoxyacetic acids by ZnO/ γ -Fe₂O₃ nanocatalysts: A comparative study. *Int. J. Chem.* 2013, 5, 56-65
34. Gupta S.S., Chakraborty I., Maliyekkal S.M., Mark T.A., Pandey D.K., Das S.K., Pradeep T., Simultaneous dehalogenation and removal of persistent halocarbon pesticides from waste water using grapheme nanocomposites: A case study of linade. *Sustainable Chem. Eng.* 2015, 3, 1155-1163.
35. Fouad D.M., and Mohamed M.B., Comparative study of the photocatalytic activity of semiconductor nanostructures and their hybrid metal nanocomposites on the photodegradation of malathion. *J. Nanomater.* 2012, doi:10.1155/2012/524123
36. Gupta V.K., Eren T., Atar N., Yola M.L., Parlak C., and Maleh H.K., CoFe₂O₄@TiO₂ decorated reduced grapheneoxide nanocomposites for photocatalytic degradation of chlorpyrifos. *J. Mol. Liquids.* 2015, 208, 122-129.
37. Sahithya K., Das D., and Das N., Effective removal of dichlorvos from aqueous solution using biopolymer modified MMT-CuO composites: Equilibrium, kinetic and thermodynamic studies. *J. Mol. Liq.* 2015, 211, 821-830.
38. Saifuddin N., Nian C.Y., Zhan L.W., and Ning K.X., Chitosan-silver nanoparticles composite as point-of-use drinking water filtration system for household to remove pesticides in water. *Asian J. Biochem.* 2011, 6, 142-159.
39. Dehaghi S.M., Rahmanifar B., Moradi A.M., and Azar P.A., Removal of permethrin pesticide from water by chitosan-zinc oxide nanoparticles composite as an adsorbent. *J. Saudi Chem. Soc.* 2014, 18, 348-355.
