

# Efficient Removal of Cationic Dye on *k*-carrageenan –based Hydrogel

E. Fosso-Kankeu\*, C.M. Koen and S. Pandey

**Abstract**—In the present work, the synthesis of *k*-carrageenan –crosslinked poly(acrylonitrile co-acrylamide) hydrogel through copolymerization of acrylonitrile and acrylamide. The optimum conditions for the synthesis of *k*-carrageenan –crosslinked poly(acrylonitrile co-acrylamide) hydrogel were determined by varying several parameters such as monomers, cross linker, initiator and reaction time.

The structure and morphology of the synthesized hydrogel and the exposed hydrogel (containing Brilliant Green) were characterized by FT-IR and adsorption experiments were carried out using various adsorbent dosages. The adsorption kinetics results showed that the adsorption followed pseudo-second order, this implies that the adsorption of the dye took place through chemisorption mechanism.

**Keywords**—Biopolymer; Hydrogel; Graft co-polymerisation; Adsorption

## I. INTRODUCTION

Water contamination is a reoccurring issue, which is often not taken seriously and affects public health and the environment [1]. Worldwide water pollution has been the cause of multiple deaths and diseases, killing about 14000 people daily, that is approximately more than 5 million people yearly [2; 3]. This global environmental issue is caused by numerous pollutants that pollute water resources [1; 4-19].

Water pollution are mainly due to chemical contamination, from industrial or domestic effluents, agricultural fertilizers that contributes to eutrophication and untreated sewage and waste, that are discharged into the water sources [20].

Chanelle M Koen is with the Water Pollution Monitoring and Remediation Initiatives Research Group, School of Chemical and Minerals Engineering, North-West University, Potchefstroom-South Africa.

Elvis Fosso-Kankeu is with the Water Pollution Monitoring and Remediation Initiatives Research Group, School of Chemical and Minerals Engineering, North-West University, Potchefstroom-South Africa.

Sadanand Pandey is with the Department of Chemistry, College of Natural Science, Yeungnam University, 280 Daehak-Ro, Gyeongsan, Gyeongbuk, 38541, Republic of Korea.

Water quality and water sources play a cardinal role in South Africa due to the physical shortage of clean and available water [21]. Multiple factors contribute to the growing shortage of water such as climate change within regions and infrequent rainfall [22]. Physical shortage of water could also be due to the increase in pollutants caused by mining industries, manufacturing industries, agriculture and untreated waste and sewage [21].

One of the largest water contamination contributors is the discharge of dyes into receiving water due to domestic and textile industrial pollution. Textile dyeing, the dyeing of material such as fabrics, fibers, cotton and yarns, is a major water contaminant which is unknown to most people [23; 24].

Dyes are classified into various classes mainly natural dyes and synthetic dyes [25]. The major sources of natural dyes are derived from plants but can also be derived from other natural resources and is broadly classified as animal, mineral and microbial dyes [26].

Synthetic dyes are made from organic molecules and are not found in nature and are therefore categorized as man-made dyes [27; 28].

The colored dye effluent that is discharged into the environment is toxic, causes skin allergies, is mutagenic to humans, carcinogenic and is harmful to aquatic life even at low concentrations [23; 29]. Adsorption is only as good as the adsorbent used in the adsorption process. Therefore, various adsorbents are available on the market which include clay materials, maize cob, starch, sawdust and hydrogels [30-32]. Different adsorbents will have different effectiveness, cost and will yield different results.

Adsorption technique will be used in this study to adsorb a cationic dye (Brilliant Green) on a *k*-carrageenan-crosslinked polyacrylonitrile co-polyacrylamide hydrogel.

The objectives in the study are the synthesis and characterization of the *k*-carrageenan–crosslinked (polyacrylonitrile co-polyacrylamide) hydrogel for dye removal from waste water.

## II. MATERIALS AND EXPERIMENTAL METHODS

### A. Materials

Acrylamide, acrylonitrile, N, N'-methylenebis-acrylamide (MBA) and Brilliant Green were purchased from Sigma-Aldrich, in South Africa. Acetone was purchased from Rochelle Chemicals & Lab Equipment C.C, in South Africa. Ammonium persulphate (APS), k-carrageenan, sodium hydroxide (used to increase the pH) and hydrochloric acid (used to reduce the pH) were provided by the laboratory of the school of chemical and minerals engineering at the North-West university, in South Africa.

### B. Synthesis of k-carrageenan based hydrogel

The k-carrageenan - crosslinked poly(acrylonitrile co-acrylamide) hydrogel was prepared through copolymerization, which entails the grafting of the acrylonitrile and acrylamide monomers by an ammonium persulphate initiator (APS) followed by crosslinking (in the presence of a crosslinker methylene bis acrylamide (MBA)) onto the biopolymer, k-carrageenan [32-35; 36].

For the synthesis of the hydrogel, 3 mL acrylonitrile and 0.5 g acrylamide were respectively dissolved in 2.0 mL and 5.0 mL distilled water, in 28 mL glass vials. The two solutions were added together into a 100 mL beaker and placed on a magnetic stirrer which stirred the solution for 5 minutes. The solution in the 100 mL beaker was continuously stirred at 750 rpm on the magnetic stirrer until all the reagents were added.

0.5 g of K-carrageenan was then dissolved in 10.0 mL warm distilled water in a 50 mL beaker. The dissolved k-carrageenan was then added to the acrylonitrile and acrylamide reaction mixture, which was stirred for 5 minutes. After 5 minutes, 0.02 g of APS, dissolved in 10.0 mL distilled water in a 28 mL glass vial, was added to the reaction mixture and stirred for 1 minute. 0.03 g of MBA, dissolved in 5 mL distilled water in a 28 mL glass vial, was then added to the reaction mixture and was stirred for 5 minutes. Whilst stirring was taking place the temperature was maintained at room temperature, 25 °C. After the mixing of the chemical components, the hydrogel was poured out into a 100 mL Duran bottle and placed in the shaking incubator, for polymerization to take place, at a temperature of 65 °C and 180 rpm shaking speed.

The reaction mixture was then left for 5 hours in the mixing state, in the shaking incubator, where after the polymerization was completed and a hydrogel formed. The polymer hydrogel was taken out of the shaking incubator and 100 mL acetone was added to the polymerized hydrogel. The acetone that was added to the hydrogel made the cutting of the gel easy, making it possible to divide the gel into smaller fragments. The hydrogel was immersed in acetone for 12 to 15 hours, to remove excess and unreacted monomers.

After the washing process (hydrogel in acetone) the product was drained from the solution through a 11 cm filter paper (with a retention of 2.5 µm and a filtration speed of 124 seconds) and was then placed on a baking tray on top of a 32 cm filter paper (with a medium retention and flow speed of 11 µm). The baking tray with the product was placed in a hot air oven and was dried at a temperature of 50 °C to 60 °C, until a constant weight was achieved, and the hydrogel was dry enough to crush. Swelling studies were then done on the synthesized hydrogel to determine the swelling capacity of the hydrogel.

### C. Preparation of dye solution

The dye solutions used in the adsorption process was prepared by diluting 100 mg of the specific desired dye in 1 L (100 ppm,) distilled water. 50 mL of this dye stock solution was then poured into 250 mL Erlenmeyer flasks and was further used in the adsorption process [4].

### D. Adsorption of Brilliant Green dye

Adsorption was carried out for the removal of brilliant green from solutions using the hydrogel. 50 mL of the stock solution was added to a 250 mL erlenmeyer flask together with 0.04 g of the adsorbent, the solution was then placed in the shaking incubator at a temperature of 25 °C for 60 minutes at a shaking speed of 160 rpm [37]. After 60 minutes in the shaking incubator 20 mL of the 50 mL solution was poured into a centrifuge tube, then centrifuged (Rotofix 32 A) for 10 mins at a speed of 4 000 rpm. After the centrifugation process, the liquid from the centrifuge tube was transferred into a clean centrifuge tube, without transferring any solid gel particles. 3 mL of the clean solution, without particles, were transferred into a cuvette and placed into the Genesys UV/Vis spectrophotometer, recording the absorbance at  $\lambda_{max}$  = 425 nm, the absorbance of the dye that was measured were then related to concentration (mg/L) using standard calibration curves.

Equation 1 and Equation 2 were used to determine the adsorption efficiency (percentage of dye removal) of the hydrogel and the adsorption capacity ( $q_e$ ) [37]:

$$\% \text{ Removal of dye} = \frac{C_0 - C_e}{C_0} \times 100 \quad (1)$$

$$q_e = \frac{C_0 - C_e}{m} \times V \quad (2)$$

$C_0$  is the initial concentration of the dye solution (mg/L),  $C_e$  is the final concentration of the dye solution (mg/L),  $V$  is the dye solution volume (L) and  $m$  the weight (g) of the dry adsorbent [37-45].

Equation 3 is the adsorption capacity ( $q_t$  (mg/g)) at time  $t$  (min), the adsorption capacity is used to

determine the concentration of Brilliant Green after recorded time intervals.

$$q_t = \frac{C_0 - C_t}{m} \times V \quad (3)$$

$C_t$  is the remaining dye concentration in the solution at a given time.

The adsorbent studies were done on the best synthesized hydrogel, together with the BG dye. The best adsorption conditions were obtained by varying different experimental parameters and the effects thereof. Adsorption of the dye onto the hydrogel was therefore studied by varying different parameters such as; time (in the shaking incubator) over a range of 10-180 min, adsorbent dose over a range of 25 mg – 70 mg. The experiments were carried out in duplicate to ensure repeatability.

### E. CHARACTERIZATION (INSTRUMENTATION)

#### FTIR

FT-IR spectra of *k*-carrageenan -crosslinked poly(acrylonitrile -co-acrylamide) based hydrogel and *k*-carrageenan based hydrogel loaded with BG dye samples were tested using the Thermo Fisher Smart iTR, Nicolet Is10 spectrophotometer made; with a frequency range of 650 – 4000  $\text{cm}^{-1}$  [37-44].

## III. RESULTS AND DISCUSSION

### A. FTIR

The FT-IR spectra of the loaded and unloaded hydrogel is shown in Fig. 1 and Fig. 2 respectively.

Before adsorption of the dye the hydrogel shows a peak at 3331  $\text{cm}^{-1}$ , which is related to -OH stretching. The peak at 1673  $\text{cm}^{-1}$  are characteristics of carboxylate groups (asymmetric and symmetric) and the strong peak is for C=C groups. The peak detected at 1223  $\text{cm}^{-1}$  refers to stretching vibration of the C-N groups. the peak at 922  $\text{cm}^{-1}$ , can be ascribed to C=N and C-C stretching vibrations of the imidazole ring. The peak at 697  $\text{cm}^{-1}$  refers to stretching vibrations of the C-N groups, the peak at 841  $\text{cm}^{-1}$  refers to out of plane bending vibration of the C-H group in the imidazole ring and the peak at 1034  $\text{cm}^{-1}$  refers to in-plane bending vibration of the C-H groups [37].

After adsorption a peak at 1580  $\text{cm}^{-1}$  was observed which refers to the stretching vibration of C=C groups of a benzene ring and at 1343  $\text{cm}^{-1}$  an aromatic tertiary amine appeared. At an adsorption peak of 1154  $\text{cm}^{-1}$  C-H bending in the benzene ring appeared [37].

The adsorption peaks shifted after adsorption of the Brilliant Green dye.



Fig. 1: FT-IR of loaded hydrogel




Fig. 2: FT-IR of unloaded hydrogel

### B. Swelling of the hydrogel

The best swelling during hydrogel synthesis was experienced at a pH of 11, concentration of biopolymer (*k*-carrageenan) of 0.5 g, an initiator APS value of 0.02 g and 3 mL of the monomer acrylonitrile.

### C. Adsorption study of BG dye: Effect of the adsorbent dose

**Error! Reference source not found.**, displays the effect of the hydrogel dosage on the % dye removal. The maximum dye removal was 93 % at an adsorbent dosage of 50 mg and 70 mg. However, 40 mg was used further in the adsorption process, due to 40 mg having the optimum (92.5 %) dye removal efficiency. The % dye removal increases as the adsorbent dose increases, this is due to more surface area and active sites being present as the amount of the hydrogel increases. There was however not a major increase in % dye removal with the increase in hydrogel dose [37; 46].

D. Adsorption kinetics




Fig. 3: Effect of adsorbent dose on adsorption

Kinetic models are established to determine the rate-controlling step of the adsorption process [24].

The pseudo-first order can be presented by Equation 4 and the pseudo-second order can be presented by Equation 5.

$$\ln(q_e - q_t) = \ln q_e - K_1 t \quad (4)$$

$$\frac{t}{q_t} = \frac{1}{K_2 q_e^2} + \frac{t}{q_e} \quad (5)$$

The amount of Brilliant Green adsorbed onto the adsorbent surface at time t (at equilibrium) is represented as  $q_e$  and  $q_t$ . The adsorption rate constants of the pseudo-first and second order are given as  $K_1$  (1/min) and  $K_2$  (g/mgmin).

The pseudo-first and second order were compared to one another and it was evident that the pseudo-second order, Fig. 5, fit better to the experimental data ( $R^2 = 0.956$ ) than the pseudo-first order ( $R^2 = 0.252$ ), Fig. 4. Implying the mechanism of adsorption is chemisorption [47-51].




Fig. 4: Adsorption Kinetics-Pseudo-first order model




Fig. 5: Adsorption Kinetics-Pseudo-second order model

IV. CONCLUSION

The present work established that efficient removal of cationic dye (BG) on *k*-carrageenan –crosslinked poly (acrylonitrile-co-acrylamide) hydrogel is possible. The optimum dosage for adsorption (dye removal) was observed to be 40 mg and considering the adsorption kinetics, the pseudo-second order fits the experimental data best.

ACKNOWLEDGEMENT

The authors are thankful to the North-West University for the support, and Mr Nico Lemmer for the laboratory assistance.

REFERENCES

- [1] Chowdhury, A.N., Jesmeen, S.R. & Hossain, M.M. 2004. Removal of dyes from water by conducting polymeric adsorbent. *Polymers for advance technologies*, 15(11):633-638. <https://doi.org/10.1002/pat.521>
- [2] Chaundry, F.N. & Malik, M.F. 2017. Factors affecting water pollution. *Journal of ecosystem &ecography*, 7(1):225.
- [3] Gleick, P.H. 2002. Dirty Water: Estimated Deaths from Water-Related Diseases 2000-2020 Pacific Institute Research Report. [https://pacinst.org/reports/water\\_related\\_deaths/water\\_related\\_deaths\\_report.pdf](https://pacinst.org/reports/water_related_deaths/water_related_deaths_report.pdf) Date of access: 24 Feb. 2019.
- [4] Sharma, P. & Das, M.R. 2012. Removal of a Cationic Dye from Aqueous Solution Using Graphene Oxide Nanosheets: Investigation of Adsorption Parameters. *Journal of Chemical & Engineering Data*, 58 (1):151–158.
- [5] Elvis Fosso-Kankeu. 2019. Nano and Bio-based Technologies for wastewater treatment: Prediction and Control Tools for the dispersion of Pollutants in the Environment. Wiley Scrivener. ISBN: 978-1-119-57709-6. Pp 301-336.
- [6] Elvis Fosso-Kankeu. 2019. New Horizons in Wastewaters Management: Emerging Monitoring and Remediation Strategies. Nova Science Publishers. ISBN: 978-1-53615-659-1.
- [7] Nthambeleni Mukwevho, Elvis Fosso-Kankeu, Frans Waanders, Neeraj Kumar, Suprakas Sinha Ray, Xavier Yangkou Mbianda. 2019. Evaluation of the photocatalytic activity of Gd<sub>2</sub>O<sub>3</sub>.ZnO.CuO nanocomposite used for the degradation of phenanthrene. Springer Nature Applied Sciences. <https://doi.org/10.1007/s42452-018-0012-0>. 1-10.

- [8] Fosso-Kankeu E., Potgieter J. and Waanders F.B. 2019. Removal of malachite green and toluidine blue dyes from aqueous solution using a clay-biochar composite of bentonite and sweet sorghum bagasse. *International Journal of Applied Engineering Research*. 14(6): 1324-1333.
- [9] Kolela J Nyembwe, Elvis Fosso-Kankeu, Frans Waanders, Kasongo D Nyembwe. 2019. Structural, compositional and mineralogical characterisation of carbonatitic copper sulfide concentrator plant streams: Run of mine, concentrate and tailings. *International Journal of Minerals, Metallurgy and Materials*. 26(2): 143-151.  
<https://doi.org/10.1007/s12613-019-1718-8>
- [10] Johannes Cornelius van der Linde, Elvis Fosso-Kankeu, Gerhard Gericke, Frans Waanders, Louise Dreyer, Nico Lemmer. 2019. Flocculant types and operating conditions influencing particles settling rates in feed water used at a coal power plant. *Desalination and Water Treatment*. 150: 293-300.  
<https://doi.org/10.5004/dwt.2019.23735>
- [11] Assumpta Chinwe Nwanya, Miranda M. Ndipingwi, Noluthando Mayedwaa, LC Razanamahandry, Chinwe O Ikpo, Tesfaye Waryo, SKO Ntwampe, E Malenga, E Fosso-Kankeu, Fabian I Ezema, Emmanuel I Iwuoha, Malik Maaza. 2019. Maize (*Zea mays* L.) fresh husk mediated biosynthesis of copper oxides: Potentials for pseudo capacitive energy storage. *Electrochimica Acta*. 301: 436-448.  
<https://doi.org/10.1016/j.electacta.2019.01.186>
- [12] LC Razanamahandry, CT Onwordi, W Saban, AKH Bashir, L Mekuto, E Malenga, E Manikandan, E Fosso-Kankeu, M Maaza, SKO Ntwampe. 2019. Performance of various cyanide degrading bacteria on the biodegradation of free cyanide in water. *Journal of Hazardous Materials*. 380: 1-6.  
<https://doi.org/10.1016/j.jhazmat.2019.120900>
- [13] IG Erdogan, L Mekuto, SKO Ntwampe, E Fosso-Kankeu, FB Waanders. 2019. Metagenomic profiling dataset of bacterial communities of a drinking water supply system (DWSS) in the arid Namaqualand region, South Africa: Source (lower Orange River) to point-of-use (O'kiep). *Journal of Data in Brief*. 25: 104135-104140.  
<https://doi.org/10.1016/j.dib.2019.104135>
- [14] N Kumar, E Fosso-Kankeu, SS Ray. 2019. Achieving controllable MoS<sub>2</sub> nanostructures with increased interlayer spacing for efficient removal of Pb(II) from aquatic systems. *ACS Applied Materials and Interfaces*. 11: 19141-19155.  
<https://doi.org/10.1021/acsmi.9b03853>
- [15] N Mukwevho, N Kumar, E Fosso-Kankeu, F Waanders, J Bunt, SS Ray. 2019. Visible light-excitable ZnO/2D graphitic-C<sub>3</sub>N<sub>4</sub> heterostructure for the photodegradation of naphthalene. *Desalination and Water Treatment*. 163: 286-296.  
<https://doi.org/10.5004/dwt.2019.24422>
- [16] E Fosso-Kankeu, R Weideman, D Moyakhe, FB Waanders, M Le Roux, QP Campbell. 2019. Hydrothermal preparation of biochar from spent coffee grounds, and its application for the removal of cadmium from coal tailings leachate. *The Journal of the Southern African Institute of Mining and Metallurgy*. 119: 607-612.  
<https://doi.org/10.17159/2411-9717/449/2019>
- [17] R Gusain, N Kumar, E Fosso-Kankeu, SS Ray. 2019. Efficient removal of Pb(II) and Cd(II) from industrial mine water by a hierarchical MoS<sub>2</sub>/SH-MWCNT nanocomposite. *ACS Omega*. 4: 13922-13935.  
<https://doi.org/10.1021/acsomega.9b01603>
- [18] Nthambeleni Mukwevho, Rashi Gusain, Elvis Fosso-Kankeu, Neeraj Kumar, Frans Waanders, Suprakas Sinha Ray. 2019. Removal of naphthalene from simulated wastewater through adsorption-photodegradation by ZnO/Ag/GO nanocomposite. *Journal of Industrial and Engineering Chemistry*.  
<https://doi.org/10.1016/j.jiec.2019.09.030>
- [19] Erdogan IC, Fosso-Kankeu E, Ntwampe SKO, Waanders FB, Hoth N, Rand A, Farrar TJ. 2019. Households water quality in O'kiep – South Africa and community perception of related health risks. 167(2019): 145-155.  
<https://doi.org/10.5004/dwt.2019.24576>
- [20] Water Wise. 2019. Substances causing pollution in rivers. <http://www.waterwise.co.za/site/water/environment/substances.html> Date of access: 20 Feb. 2019.
- [21] Rand Water. 2019. Water pollution and your health. <http://www.randwater.co.za/CorporateResponsibility/WWE/Pages/WaterPollution.aspx> Date of access: 19 Feb. 2019.
- [22] The water project. 2019. Water in crisis-South Africa. <https://thewaterproject.org/water-crisis/water-in-crisis-south-africa> Date of access: 20 Feb. 2019.
- [23] Doltabadi, M., Alidadi, H. & Davoudi, M. 2016. Comparative study of cationic and anionic dye removal from aqueous solutions using sawdust-based adsorbent. *Environmental Progress & Sustainable Energy*, 35(4):1078-1090.
- [24] Kant, R. 2012. Textile dyeing industry an environmental hazard. *Natural Science*, 4(1):22-26.  
<https://doi.org/10.4236/ns.2012.41004>
- [25] Textile Learner. 2019. Dyeing Process | Different Types of Dyes | Classification of Dyes [http://textilelearner.blogspot.com/2011/07/dyeing-process-different-types-of-dye\\_1720.html?m=1](http://textilelearner.blogspot.com/2011/07/dyeing-process-different-types-of-dye_1720.html?m=1) Date of access: 20 Feb. 2019.
- [26] Saxena, S. & Raja, A.S.M., Muthu S. eds. 2014. Roadmap to Sustainable Textiles and Clothing. Singapore: Springer.
- [27] Bernard, J.P. 2016. Where do synthetic organic dyes come from? <http://www.fsw.cc/where-synthetic-organic-dyes-from/> Date of access: 25 Feb. 2019.
- [28] Gravelet-Blondin, L.R., Barclay, S.J., Carliell, C.M. & Buckley, C.A. 1998. Management of water resources in South Africa with respect to the textile industry. *Water science and technology*, 36(2-3):303-310.  
<https://doi.org/10.2166/wst.1997.0544>
- [29] Ghani, M., Rezaei, B., Aghaji, A.G. & Arami, M. 2016. Novel Cross-linked Superfine Alginate-Based Nanofibres: Fabrication, Characterization, and Their Use in the Adsorption of Cationic and Anionic Dyes. *Advance polymer technology*, 35(4):428-438.  
<https://doi.org/10.1002/adv.21569>

- [30] Delval, F., Crini, G., Vebrel, J., Knorr, M., Sauvin, G. & Conte E. 2003. Starch-modified filters used for the removal of dyes from waste water. *Special Issue: Polymer-Solvent Complexes and Intercalates IV*, 203(1):165-172.
- [31] Minisy, I.M., Salahuddin, N.A. & Ayad M.M. 2018. Chitosan/polyaniline hybrid for the removal of cationic and anionic dyes from aqueous solutions. *Journal of Applied Polymer Science*, 136(6).
- [32] Senkal, B.F., Erkal, D. & Yavuz, E. 2006. Removal of dyes from water by poly(vinyl pyrrolidone) hydrogel. *Polymers for advance technologies*, 17(11-12):924-927. <https://doi.org/10.1002/pat.836>
- [33] Aldalbahi, A., Chu, J., Feng, P. & Panhuis, M.I.H. 2012. Conducting composite materials from the biopolymer kappa-carrageenan and carbon nanotubes. *Beilstein journal of nanotechnology*, 3(1):415-427. <https://doi.org/10.3762/bjnano.3.48>
- [34] All about acrylonitrile. 2013. About Acrylonitrile Products. <http://angroup.org/about/index.php> Date of access: 24 July 2019.
- [35] Aramwit, P. 2016. Introduction to biomaterials for wound healing. <https://www.sciencedirect.com/topics/materials-science/carrageenans> Date of access: 25 Feb. 2019.
- [36] Ver Vers, L.M. 1999. Determination of Acrylamide Monomer in Polyacrylamide Degradation Studies by High-Performance Liquid Chromatography. *Journal of Chromatographic Science*, 37(1): 486-494. <https://doi.org/10.1093/chromsci/37.12.486>
- [37] Mohamed, R.R., Abu Elella, M.H., Sabaa, M.W. & Saad, G.R. 2018. Synthesis of an efficient adsorbent hydrogel based on biodegradable polymers for removing crystal violet dye from aqueous solution. *Cellulose*, 25(11):6513-6529. <https://doi.org/10.1007/s10570-018-2014-x>
- [38] E. Fosso-Kankeu, A.F. Mulaba-Bafubiandi, B.B. Mamba and T.G. Barnard, Prediction of metal-adsorption behaviour in the remediation of water contamination using indigenous microorganisms. *Journal of Environmental Management*. Vol. 92, no. 10, pp. 2786-2793, 2011. <https://doi.org/10.1016/j.jenvman.2011.06.025>
- [39] H. Mittal, E. Fosso-Kankeu, Shivani B. Mishra, Ajay K. Mishra, Biosorption potential of Gum ghatti-g-poly (acrylic acid) and susceptibility to biodegradation by *B. subtilis*. *International Journal of Biological Macromolecules*. Vol. 62, pp. 370-378, 2013. <https://doi.org/10.1016/j.ijbiomac.2013.09.023>
- [40] E. Fosso-Kankeu, A.F. Mulaba-Bafubiandi, Implication of plants and microbial metalloproteins in the bioremediation of polluted waters. *Journal of Physics and Chemistry of the Earth*. Vol. 67-69, 242-252, 2014. <https://doi.org/10.1016/j.pce.2013.09.018>
- [41] E. Fosso-Kankeu, H. Mittal, S.B. Mishra, A.K. Mishra, Gum ghatti and acrylic acid based biodegradable hydrogels for the effective adsorption of cationic dyes. *Journal of Industrial and Engineering Chemistry*. Vol. 22, pp. 171-178, 2015. <https://doi.org/10.1016/j.jiec.2014.07.007>
- [42] E. Fosso-Kankeu, H. Mittal, F. Waanders, I.O. Ntwampe, S.S. Ray, Preparation and characterization of gum karaya hydrogel nanocomposite flocculant for metal ions removal from mine effluents. *International Journal of Environmental Science and Technology*. Vol. 13, pp. 711-724, 2016. <https://doi.org/10.1007/s13762-015-0915-x>
- [43] E. Fosso-Kankeu, F. Waanders, E. Maloy, Copolymerization of ethyl acrylate onto guar gum for the adsorption of Mg(II) and Ca(II) ions. *Desalination and Water Treatment*. doi: 10.1080/19443994.2016.1165147: pp. 1-10, 2016.
- [44] E. Fosso-Kankeu, F. Waanders, C.L. Fourie, Adsorption of Congo Red by surfactant-impregnated bentonite clay. *Desalination and Water Treatment*. doi: 10.1080/19443994.2016.1177599: pp. 1-9, 2016.
- [45] Hu, X.S., Liang, R., & Sun, G. 2018. Super-adsorbent hydrogel for removal of methylene blue dye from aqueous solution. *J. Mater. Chem. A. Royal Society of Chemistry*. 6(36):17612-17624. <https://doi.org/10.1039/C8TA04722G>
- [46] Shirsath, S.R., Patil, A.P., Patil, R., Naik, J.B., Gogate, P.R., & Sonawane, S.H. 2013. Removal of Brilliant Green from wastewater using conventional and ultrasonically prepared poly(acrylic acid) hydrogel loaded with kaolin clay: A comparative study. *Ultrason. Sonochem. Elsevier B.V.* 20(3):914-923. <https://doi.org/10.1016/j.ultsonch.2012.11.010>
- [47] E. Fosso-Kankeu, A.F. Mulaba-Bafubiandi, L.A. Piater, M.G. Tlou, Cloning of the *cnr* operon into a strain of Bacillaceae bacterium for the development of a suitable biosorbent. *World Journal of Microbiology and Biotechnology*. DOI 10.1007/s11274-016-2069-5. 2016.
- [48] E. Fosso-Kankeu, H. Mittal, F. Waanders, S.S. Ray, Thermodynamic properties and adsorption behaviour of hydrogel nanocomposites for cadmium removal from mine effluents. *Journal of Industrial and Engineering Chemistry*. Vol. 48, pp. 151-161, 2017. <https://doi.org/10.1016/j.jiec.2016.12.033>
- [49] E. Fosso-Kankeu, F.B. Waanders, F.W. Steyn, Removal of Cr(VI) and Zn(II) from an aqueous solution using an organic-inorganic composite of bentonite-biochar-hematite. *Desalination and Water Treatment*. Vol. 59, pp. 144-153, 2017. <https://doi.org/10.5004/dwt.2017.0059>
- [50] L.P. Simelane, E. Fosso-Kankeu, P. Njobeh, S. Pandey, Response of bacterial biosorbents to chemical treatment as influenced by cell membrane structure and impact on the adsorption behaviour of dyes. *Current Science*. Vol. 114, no. 4, pp. 826-834, 2018. <https://doi.org/10.18520/cs/v114/i04/826-834>
- [51] A. Leudjo Taka, E. Fosso-Kankeu, K. Pillay, X. Yangkou Mbianda, Removal of cobalt and lead ions from wastewater samples using an insoluble nanosponge biopolymer composite: Adsorption isotherms, kinetics, thermodynamics and regeneration studies. *Environmental Science and Pollution Research*. 2018.