

# AANSS2022

ANBUG-AINSE Neutron Scattering Symposium

**9<sup>th</sup> – 11<sup>th</sup> November2022**



# Contents

|  |    |
|--|----|
| Neutron scattering studies of biochar for catalysis applications 87 .....  | 1  |
| In situ SANS analysis to investigate the electric field alignment of Silver-based Solvate Ionic Liquid (SIL) and Silver Nanoparticles (AgNPs) in nanocomposites 3..... | 1  |
| The cutting edge of archaeological inquiry: Antique swords and neutron techniques 68 .   | 2  |
| The Effect of Size Reduction Induced by Mechanical Milling on Rare Earth Manganites 15   | 3  |
| In-Situ Structural Analysis of the Oxygenation of YBaCo4O7+[g 13 .....   | 3  |
| Advanced Diffraction and Scattering beamlines (ADS-1 and ADS-2): The closest thing to a neutron beam at the Australian Synchrotron? 29 .....                           | 4  |
| Disorder and ionic conductivity in Ba3Nb(M)O8.5 38 .....   | 5  |
| Top-down patterning of topological edge states using ion beam and characterization with neutron reflectometry 59.....  | 5  |
| In-house design and domestic fabrication of cryofurnace and induction furnace 85 .....   | 6  |
| DINGO, the neutron imaging instrument at ANSTO 86.....   | 7  |
| The Invisible Revealed: Cultural Forensics with Neutron Beam Science 73.....   | 8  |
| Spin Ice Behaviour in Spin Crossover Materials 31.....   | 8  |
| Deuteration of cholesterol for neutron applications 77 .....   | 9  |
| Understanding and controlling the formation of photonic crystals from polydisperse col- loidal systems 66.....   | 10 |
| Deuterium labelling at the National Deuteration Facility: Updates on Demand and Supply   |    |
| 44 . . . . .   |    |
| 10   |    |
| Using a computer game engine to teach neutron reflectometry alignment 62 .....   | 11 |
| Solution structure characterisation of the complex of ubiquitin and its conjugating enzyme E2 by deuteration and small angle neutron scattering. 78.....               | 12 |
| KOALA decommissioned October 2022 what has been achieved? and what remains to be done KOALA2 implementation underway 83.....   | 13 |
| Strengthening Oxygen Lattice to Achieve Better-Performance Cobalt-free Li-Rich Layered Oxide Cathodes 2.....   | 13 |

|   |    |
|---|----|
| Diffuse Scattering from a Martensitic Fe-Pd Alloy 11 .....  | 14 |
| Thermodynamics and local environment in liquid gallium under static magnetic fields 27 .....  | 15 |
| ACNS – Scientific Computing Services 21 .....   | 16 |
| Status, statistics, and recent research highlights from Echidna 41 .....  | 16 |
| Interrogation of the mechanism of Li-mediated ammonia electrosynthesis by in situ neutron reflectometry 19 .....  | 17 |
| Reflecting Neutrons with Platypus 81.....   | 17 |
| Revealing composition and conformation of liposomes using integrated methods of HPLC/AF4, UV-Vis absorption, Refractive Index, MALLS, DLS, and SAXS-WAXS 71 ..... | 18 |
| Reflecting Neutrons with Spatz 82 .....   | 19 |
| Thermal Treatment on Vertical Morphology of PffBT4T-2OD: ITIC Non-fullerene Bulk Heterojunction Thin Films 50.....  | 19 |
| Residual stress in multilayer laser cladding depositions on light rail components 46.....   | 20 |
| EMU cold-neutron backscattering spectrometer at ACNS, ANSTO 58 .....  | 21 |
| Experimental and numerical investigation of fracture in welded connections 8.....   | 21 |
| Multiscale structure parameters affecting phase transitions in PbZrO <sub>3</sub> -based antiferroelectric ceramics 26 .....                                      | 22 |
| A 3-D Reconstruction of neutron activation in samples irradiated at DINGO 61 .....  | 23 |
| Recent Achievements in Neutron Backscattering 1.....  | 24 |
| Neutron Polarisation Capabilities at ACNS 42 .....  | 24 |
| How ionic liquid composition and structure affect micelle morphology 74 .....   | 25 |
| Understanding nanoplastic toxicology using neutron scattering techniques. 23.....   | 26 |
| Kookaburra, the ultra-small-angle neutron scattering instrument at ANSTO: design and recent applications 24.....  | 26 |
| Deuteration as a tool for structure determination of membrane proteins 53.....  | 27 |
| Supermirror focussing guide for Pelican 32.....   | 28 |
| Neutron scattering measurements on rare earth single molecule magnets. 34.....  | 29 |
| Recent highlights from the Pelican spectrometer 33.....   | 29 |
| Neutron Diffraction at the start and end of the Nuclear Fuel Cycle 72.....  | 30 |

|   |    |
|---|----|
| Experimental and Computational Studies of Sulfided NiMo Supported on Pillared Clay: Catalyst Activation and Guaiacol Adsorption Sites 88..... | 30 |
| Update on the progress of ACNS Industrial Liaison Office and future opportunities 76.....   | 31 |
| TOPOLOGICALLY STABILIZED SPIN CONFIGURATIONS IN RARE-EARTH BASED SYSTEMS USING POLARIZED NEUTRON SCATTERING 40.....                           | 32 |
| Structures of photocycle intermediates of the orange carotenoid protein studied by small angle scattering using partial deuteration 39 .....  | 32 |
| Diverse Deuterated Lipids for Neutron Applications 54.....  | 33 |
| Recent upgrades to the Kowari strain scanner 89.....  | 34 |
| The role of the solvent in specific ion effects: PNIPAM brushes in non-aqueous electrolytes 18 . . . . .                                      | 34 |
| refnx + reflips: Analysing neutron/X-ray/light scattering from surfaces in Python 20 .....  | 35 |
| Development of the yeast platform in the NDF for expanding the range of lipids available to researchers. 64.....                              | 36 |
| Update from the Australian Centre for Neutron Scattering 69.....  | 37 |
| Cubosomes: A polytherapy based approach to combat antimicrobial resistance 47.....  | 37 |
| Investigating Allergenicity of Pollen Allergens in Thunderstorm Asthma Using Neutron Reflectometry 22 .....                                   | 38 |
| Small Angle Neutron Scattering instrument Bilby: capabilities to study mainstream and complex systems 75.....                                 | 39 |
| Magnetic non-uniformity of antiferromagnetic FeRh film from polarized neutron reflectometry 65..  | 40 |
| Phonon Engineering Thermoelectrics with Inelastic Neutron Scattering 10 .....   | 40 |
| McStas Simulations of Taipan 80.....  | 41 |
| Taipan: The Thermal Triple-Axis and Be-Filter Spectrometers 79 .....  | 42 |
| Rational Design of Advanced Nuclear Fuel Materials: New Pathways from In Situ Neutron Diffraction. 30.....                                    | 43 |
| Difference the Spot with Wombat 6.....  | 43 |
| Wombat – the high intensity diffractometer at OPAL 25 .....   | 44 |
| Investigation of the residual stress of steel after laser cleaning 37 .....   | 45 |
| Interrogation of the mechanism of Li-mediated ammonia electrosynthesis by in situ neutron reflectometry 17 .....                              | 45 |

|   |    |
|---|----|
| SAMPLE ENVIRONMENT DEVELOPMENTS FROM THE AUSTRALIAN CENTRE FOR NEUTRON SCATTERING 84.....   | 46 |
| Modelling Small-Angle Neutron Scattering of concentrated wormlike micelles 5 .....  | 47 |
| Polycation radius of gyration in a polymeric ionic liquid (PIL): the PIL melt is not a theta solvent 55.....                          | 48 |
| Quokka, the Monochromatic Small Angle Neutron Scattering instrument at ANSTO: Planned Upgrades & Scientific Highlights 56 .....       | 48 |
| GISANS to Study The Mechanism in Perforated Layers of Blend Films of a Symmetric Polystyrene-block-Poly(methyl methacrylate) 48 ..... | 49 |
| Investigation of anomalous thermal and pressure-induced distortion in spin crossover materials 4 .....                                | 50 |
| The updates from the cold neutron axis spectrometer SIKA 57 .....   | 51 |
| Vibrational Properties Beyond Debye Model 35 .....  | 51 |
| Pressure Cells for Quasielastic and Inelastic Neutron Scatterings 36 .....  | 52 |
| Structural characterization of niosome nanoparticle for ocular drug delivery 63.....  | 52 |

87

## Neutron scattering studies of biochar for catalysis applications

Indri Adilina<sup>1</sup>; Muhammad Safaat<sup>1</sup>; Ferensa Oemry<sup>1</sup>; Stewart Parker<sup>2</sup> <sup>1</sup> *National Research and Innovation Agency*

<sup>2</sup> *ISIS Neutron and Muon Source, STFC Rutherford Appleton Laboratory*

**Corresponding Author(s):** indribadria@yahoo.com

A combination of infrared, Raman and inelastic neutron scattering (INS) was carried out to achieve a complete vibrational assignment of biochar (BCR) obtained from the pyrolysis of palm oil empty fruit bunch. The CH–OH ratio in BCR is ~5, showing that the hydroxyl functional groups are a minority species. There was no evidence for any aromatic C–H stretch modes in the infrared, but they are clearly seen in the INS and are the majority species, with a ratio of sp<sup>3</sup>–CH:sp<sup>2</sup>–CH of 1:1.3. The hydrogen bound to sp<sup>2</sup>–C is largely present as isolated C–H bonds, rather than adjacent C–H bonds. The Raman spectrum shows the characteristic G band (ideal graphitic lattice) and three D bands (disordered graphitic lattice, amorphous carbon, and defective graphitic lattice) of sp<sup>2</sup> carbons. Adsorbed water in BCR is present as disordered layers on the surface rather than trapped in voids in the material and could be removed easily by drying prior to catalysis. Catalytic testing demonstrated that BCR was able to catalyse the hydrodeoxygenation of guaiacol – a lignin model compound, yielding phenol and cresols as the major products. Phenol was produced both from the direct demethoxylation of guaiacol, as well as through the demethylation pathway via the formation of catechol as the intermediate followed by deoxygenation.

## **In situ SANS analysis to investigate the electric field alignment of Silver-based Solvate Ionic Liquid (SIL) and Silver Nanoparticles (AgNPs) in nanocomposites**

Ahmed Al-Qatatsheh<sup>1</sup> ; Anna Sokolova<sup>2</sup> ; Nishar Hameed<sup>1</sup>

<sup>1</sup> *Swinburne University of Technology*

<sup>2</sup> *Dr*

**Corresponding Author(s):** aalqatatsheh@swin.edu.au

The structural design of composite matrices is necessary to optimize electrical, mechanical, and thermal properties for smart applications in various industries, including aerospace, defence, and MedTech. The induced electrical or magnetic field alignment of anisotropic fillers (e.g., Ag, Graphene) or SIL has drawn attention since they can boost composites' performance. For example, the enhancement in bulk electrical conductivity of aligned Ag nanoparticles (AgNPs) in a composite matrix can

be five orders of magnitude, converting the sample conductivity from polymer-dominated to silver-dominated.

Our work presents a comprehensive study of the impact of alignment changes of Ag (I) and AgNPs in various composite matrices under the externally applied electric field and assess the alignment's stability after the electric field is permanently removed. We studied the effect of directional alignment on creating the high crosslinked density regions in composite matrices. Furthermore, We evaluated the contributions of the high crosslinked density segments and the hierarchical structure of the aligned complexes and composite matrices' properties and performance.

In addition to the utilization of the Infrared macrospectroscopy beamline to evaluate the directional alignment using the four-angle approach, we used SANS to study the kinetic effects under external impulse influence since SANS data helped identify the clusters of Ag under an external electric field in various composite matrices. We also applied computational modeling based on quantum mechanics to validate investigation outcomes and reveal the uniqueness of the composite structure responsible for the superior properties.

## The cutting edge of archaeological inquiry: Antique swords and neutron techniques

Ron Anderson<sup>1</sup>

<sup>1</sup> *University of Sydney*

**Corresponding Author(s):** ronlawrenceanderson@gmail.com

Until recently, little has been known about swords from the historical Kingdom of Dahomey in the Bight of Benin in West Africa, an area that was otherwise known as the Slave Coast because of its unique role in the trans-Atlantic slave trade. The kingdom, which existed from about the mid-17th century to 1894, when it was conquered and subjugated by France, was one of the most intriguing and unique centralized states of pre-colonial West Africa – not least because of the all- female warrior corps that garnered it rapt worldwide attention. In what has been a world first, with a grant from ANSTO six Dahomean swords were examined using neutron techniques that were able to delve beneath the surface of the metal, uncovering insights into their manufacture that helps answer hitherto open questions on whether these swords were made with imported European iron, or not. While it is known that iron from Northern Europe was imported in significant amounts into the Gulf of Guinea throughout the period, the relative importance of those imports has been a mystery. In fact, this study suggests that European imported iron has been overvalued in the perceptions and assessments of European observers for the last 150 years, and that local African smelted iron was of far greater importance to local weapons manufacture. In addition, the research uncovered hitherto unknown data on some of the unique construction techniques employed in the manufacture of these rare and hitherto understudied historical items.



15

## The Effect of Size Reduction Induced by Mechanical Milling on Rare Earth Manganites

Mark Appletree<sup>1</sup> ; Samuel Yick<sup>2</sup> ; Ben Mallett<sup>1</sup> ; Tilo Soehnel<sup>3</sup>

<sup>1</sup> *University of Auckland*

<sup>2</sup> *UNSW and ANSTO*

<sup>3</sup> *The University of Auckland*

**Corresponding Author(s):** msmi422@aucklanduni.ac.nz

The perovskite manganites with chemical formula  $AMnO_3$  are known for strong coupling of spin, electronic, and structural degrees of freedom. These couplings manifest as extreme sensitivity in the electronic and magnetic properties with variations in structure and temperature; the colossal magnetoresistance effect being the best-known example. In particular, the phase diagram of the  $RE_{1-x}(Ca_{1-y}Sr_y)_xMnO_3$  (RE = trivalent rare-earth) system is diverse, containing insulating and metallic phases with orbital and magnetic ordering as hole doping ( $x$ ), and the structural tolerance factor, ( $t$ ) varies.

This study focuses on how mechanical milling affects the magnetic and structural properties of the manganite series  $Nd_{1-x}(Ca_{1-y}Sr_y)_xMnO_3$  (NCSMO, nominally:  $x = 0.4$ ,  $0 \leq y \leq 0.3$ ), as it is near to a magnetic phase boundary, around which an antiferromagnetic insulating state with charge and orbital ordering, and two ferromagnetic states, one metallic and one insulating with orbital ordering occur.

The magnetic and structural properties of bulk NCSMO powder have been compared against mechanically milled NCSMO powder using X-ray diffraction, PPMS, and neutron powder diffraction (WOMBAT and ECHIDNA) techniques. It has been observed that reducing the size of the crystallites via mechanical milling changes the magnetic properties of the manganite materials, even though no noticeable structural changes occur. This work presents possible mechanisms which can lead to the observed deviation to the magnetic structure.

13

## In-Situ Structural Analysis of the Oxygenation of YBaCo<sub>4</sub>O<sub>7</sub>+

Timothy Christopher<sup>1</sup> ; Tilo Soehnel<sup>2</sup> ; Saifang Huang<sup>3</sup> ; Peng Cao<sup>4</sup>

<sup>1</sup> *University of Auckland*

<sup>2</sup> *The University of Auckland*

<sup>3</sup> *UoA*

<sup>4</sup> *University of Auckland*

**Corresponding Author(s):** [msemi422@aucklanduni.ac.nz](mailto:msemi422@aucklanduni.ac.nz)

In this work, the oxygenation of YBaCo<sub>4</sub>O<sub>7+δ</sub> is further explored through neutron diffraction studies. The 114-compound material of YBaCo<sub>4</sub>O<sub>7</sub> is a mixed cobalt valence system that exists in a hexagonal arrangement (space group *P* 6<sub>3</sub> *mc*). Mixed Co<sup>2+/3+</sup> valence allows the structure to accommodate additional oxygen through a structural transition to an orthorhombic arrangement. Neutron powder diffraction patterns revealed the evolution of the oxygenated YBaCo<sub>4</sub>O<sub>7+δ</sub>,  $\delta = 1$  phase when exposed to oxygen at 320 °C. This is paired with a decrease in the YBaCo<sub>4</sub>O<sub>7+δ</sub>,  $\delta = 0$  phase due to the one formula equivalent of Co<sup>2+</sup> fully oxidising to Co<sup>3+</sup>. It results in a bulk mixture containing both  $\delta = 0$  and 1 phases. After 1 hour of exposure to oxygen at 320 °C, more than 97 % of the phase mixture is now  $\delta = 1$ . The diffraction results here show that thermogravimetric studies, while convenient, do not give the complete picture of what is happening. And understanding what exact phases of YBaCo<sub>4</sub>O<sub>7+δ</sub> are present can help with potential oxygen storage applications.

## Advanced Diffraction and Scattering beamlines (ADS-1 and ADS- 2): The closest thing to a neutron beam at the Australian Syn- chrotron?

Josie Auckett<sup>1</sup> ; Renata Lippi<sup>1</sup> ; Justin Kimpton<sup>None</sup>

<sup>1</sup> *Australian Synchrotron*

**Corresponding Author(s):** josiea@ansto.gov.au

One of the advantages of neutron radiation over X-ray radiation for diffraction, spectroscopy and imaging experiments is its superior penetration in bulky and/or high-Z samples (and sample environments). By contrast, materials characterisation experiments using typical hard X-ray beams (~8–30 keV,  $\lambda = 0.4\text{--}1.5 \text{ \AA}$ ) in transmission mode are usually limited to samples  $\leq 1 \text{ mm}$  thick, even with very high-flux synchrotron radiation sources.

The Australian Synchrotron is currently building two Advanced Diffraction and Scattering (ADS) beamlines that will offer high-energy X-rays (45–150 keV,  $\lambda = 0.08\text{--}0.27 \text{ \AA}$ ) for a wide range of diffraction, imaging and tomography experiments. These X-ray beams will penetrate up to 1 cm of aluminium or steel with 70% or 25% transmission, respectively, paving the way for more “neutron-like” experimental setups, such as strain mapping in large objects and *in situ* sample environments with metallic windows.

ADS-1 and ADS-2 are designed to be highly versatile beamlines, offering flexible instrument configurations to support diverse structural and microstructural characterisation experiments in materials science, engineering and mineralogy. The two endstations will feature multi-axis positioning systems for polycrystalline, single-crystal and monolithic samples, along with in-built gas delivery facilities and space for user-supplied equipment.

I will present an overview of the planned capabilities of the ADS beamlines and the expected timeline for their implementation, with emphasis on the complementarity of ADS with instruments such as WOMBAT, KOWARI, KOALA and DINGO.

38

## Disorder and ionic conductivity in Ba<sub>3</sub>Nb(M)O<sub>8.5</sub>

Josie E. Auckett<sup>1</sup>; Ivana R. Evans<sup>None</sup><sup>1</sup> *Australian Synchrotron***Corresponding Author(s):** josiea@ansto.gov.au

Understanding atomic-scale structure and local defect distributions in functional materials, such as ionic conductors, is essential for rationalising their behaviour and tuning them for better performance. We have grown the first single crystals of the oxide-ionic conductors Ba<sub>3</sub>NbMoO<sub>8.5</sub> and Ba<sub>3</sub>NbWO<sub>8.5</sub> in order to investigate the relationship between the highly disordered average Ba<sub>3</sub>Nb(M)O<sub>8.5</sub> structure and the arrangements of ions on the local scale. Our neutron scattering experiments on single-crystal and polycrystalline samples yield several important insights into the local cation and anion arrangements, which are deduced after taking into consideration both chemical and geometric constraints. Our data also inform the interpretation of calculated bond valence energy landscape (BVEL) maps, which point to a high degree of oxide ion disorder along two- or three-dimensional conduction pathways. These findings highlight the need for a more flexible description of oxide ion distributions in the Ba<sub>3</sub>Nb(M)O<sub>8.5</sub> structure than is conventionally used in the literature.

## Top-down patterning of topological edge states using ion beam and characterization with neutron reflectometry

Abduliken Bake<sup>1</sup> ; Qi Zhang<sup>2</sup> ; Cong Son Ho<sup>3</sup> ; Grace Causer<sup>4</sup> ; Weiyao Zhao<sup>5</sup> ; Zengji Yue<sup>1</sup> ; Alexander Nguyen<sup>5</sup>

; Golrokh Akhgar<sup>5</sup> ; Julie Karel<sup>5</sup> ; David Mitchell<sup>1</sup> ; Zeljko Pastuovic<sup>6</sup> ; Roger Lewis<sup>1</sup> ; Jared Cole<sup>3</sup> ; Mitchell Nancarrow<sup>1</sup> ; Nagarajan Valanoor<sup>2</sup> ; Xiaolin Wang<sup>1</sup> ; David Cortie<sup>7</sup>

<sup>1</sup> *University of Wollongong*

<sup>2</sup> *University of New South Wales*

<sup>3</sup> *RMIT*

<sup>4</sup> *TUM*

<sup>5</sup> *Monash University*

<sup>6</sup> *ANSTO*

<sup>7</sup> *The University of Wollongong*

**Corresponding Author(s):** ab913@uowmail.edu.au

Amorphous states in topological insulators have recently emerged as a point of intense discussion, and whether they are topological or trivial is currently of great interest. This question is crucial as it determines whether they behave as a “topological vacuum” to enable surface lithographic patterning via spatial control over  $\mathbb{Z}_2$ . Recent theories predict that the collapse of the topological states in the glass is not guaranteed. Instead, solid-state amorphous topological insulators do exist in exceptional cases, at least in numerical simulations. Therefore, it is crucial to understand how amorphization modifies the strong TIs in the crystalline chalcogenide family (Bi<sub>2</sub>Se<sub>3</sub>, Sb<sub>2</sub>Te<sub>3</sub> and Bi<sub>2</sub>Te<sub>3</sub>). Here it is experimentally shown that targeted modification with an ion beam at the surface of Sb<sub>2</sub>Te<sub>3</sub> locally switches the strong 3D crystalline topological insulator into an insulating amorphous state with negligible bulk and surface conductivity. This is attributed to a transition from  $\mathbb{Z}_2=1 \rightarrow \mathbb{Z}_2=0$  at a critical disorder strength that drives a topological transition, as supported by density functional theory from ab initio molecular dynamics and model Hamiltonian calculations. This allows for the patterning of lateral heterostructures, and remarkably, the boundary of the amorphous and crystalline region gives rise to additional edge state conductivity that can be detected at room temperature. The ability to drive the topological transition and modulate the surface conductivity in real space with a phase-change material is useful: it allows for inverse lithography to write topological surfaces, edges, and corners which are the future building blocks of scalable topological electronics.

## In-house design and domestic fabrication of cryofurnace and induction furnace

**Author(s):** Chris Baldwin<sup>1</sup>

**Co-author(s):** Rachel White <sup>1</sup>; Timothy D'Adam <sup>2</sup>; Gene Davidson <sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> ACNS, ANSTO

**Corresponding Author(s):** baldwinc@ansto.gov.au, rew@ansto.gov.au

As part of the Australian Government's research infrastructure and investment plan (RIIP), ACNS has acquired several new bespoke sample environments for high and low temperature experiments. We have designed from scratch a 4K to 800K cryofurnace and a 300K to 1273K induction furnace, which are currently being commissioned.

By designing these systems from the ground up we are able to tailor them to our specific operational needs and gain the ability to freely source spare parts and make future modifications.

## DINGO, the neutron imaging instrument at ANSTO

Joseph Bevitt<sup>1</sup> ; Filomena Salvemini<sup>1</sup> ; Mark Reid<sup>1</sup> ; Ulf Garbe<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** joseph.bevitt@ansto.gov.au, filomena.salvemini@ansto.gov.au, mark.reid@ansto.gov.au, ulf.garbe@ansto.gov.au

Since receiving first neutrons in October 2014, the thermal-neutron radiography/tomography/imaging instrument DINGO [1] has achieved a high subscription rate from a broad national and international research community. The high demand for DINGO is based upon the different insights achieved when looking into objects because of the different contrast achieved with neutrons compared to X-rays, the high sensitivity of neutrons to light elements, and the dedicated expertise of the instrument staff.

DINGO has shown real value in industrial applications, particularly in the structural analysis of cracks and defects in concrete, metals and complex composite materials. Originally designed to achieve a true spatial resolution of 54–200 µm for samples up to 35 cm in height, a combination of instrument upgrades now enables ANSTO to offer a globally unique, parallelised and high-throughput scanning capability for drillcores and samples up to 1m in length, improved signal-to-noise and spatial resolution, a larger field-of-view and the flexibility to incorporate sample environments for kinetic and real-world studies.

With a strong and research-active support team, DINGO is the global go-to facility for the application of thermal-neutron imaging in palaeontology, cultural heritage, mining, energy storage and commercial applications, exemplified through high-impact research outputs, major museum exhibitions, and reports in the media.

This poster presents an overview of the DINGO instrument and its technical capabilities, highlights a selection of research achievements from the collaborative, merit-based user access program. Come, meet our team and give neutron tomography a try!

[1] Garbe, U; Randall, T; Hughes, C; Davidson, G; Pangelis, S and Kennedy, SJ, A New Neutron Radiography / Tomography / Imaging Station DINGO at OPAL, Physics Procedia 69, 27 (2015).

## The Invisible Revealed: Cultural Forensics with Neutron Beam Science

**Author(s):** Joseph Bevitt<sup>1</sup>

**Co-author(s):** Tomasz Bednarz <sup>2</sup> ; Deborah Lawler-Dormer <sup>3</sup>

<sup>1</sup> ANSTO

<sup>2</sup> NVIDIA

<sup>3</sup> Museum of Applied Arts and Sciences

**Corresponding Author(s):** joseph.bevitt@ansto.gov.au

The Powerhouse Museum in Sydney houses more than half a million objects of cultural significance, spanning 3000+ years of human technological advancement. “The Invisible Revealed” exhibition (Nov 2021 - Sep 2022) evolved through a partnership between the Museum, ANSTO and the Expanded Perception and Interaction Centre at UNSW. It is the first major museum research exhibition for ANSTO, and internationally, the first to showcase neutron imaging. It presents 26 of the Museum’s objects alongside digital 3D models produced using innovative neutron- and synchrotron- X-ray tomography, photogrammetry, Digital Twin technology, Artificial Intelligence, and other insights achieved with nuclear methods.

This talk provides an overview of neutron imaging and complementary methods applied in this national-award winning exhibit, and demonstrates the hidden mechanisms, repairs, degradation and insights gleaned in miniature spy cameras, a Tang Dynasty statue, early coinage and more.



31

## Spin Ice Behaviour in Spin Crossover Materials

Andrew Braz<sup>1</sup>; Vanessa Peterson<sup>2</sup>; Suzanne Neville<sup>1</sup>; Richard Mole<sup>2</sup>; Cameron Kepert<sup>1</sup>; Natasha Sciortino<sup>1</sup>; Jace Cruddas<sup>3</sup>; Ben Powell<sup>3</sup>

<sup>1</sup> *The University of Sydney*

<sup>2</sup> *ANSTO*

<sup>3</sup> *The University of Queensland*

**Corresponding Author(s):** abra8126@uni.sydney.edu.au

Metal-Organic Frameworks (MOFs) are a class of compounds that have received increased interest over the last few decades due to the multitude of properties they exhibit. This work primarily focused on the suspected spin ice system,  $\text{Fe}(\text{Ag}(\text{CN})_2)(\text{dps})_2 \cdot 2\text{EtOH}$ , (dps = 4,4'-dipyridylselenide). In this structure elastically coupled Fe(II) ions are mapped on a triangular Kagome-like array, leading to a deviation from the conventional low spin-high spin (LS-HS) structure seen in mixed spin-state (multi-step) spin crossover systems. Here, competing long-range ferroelastic interactions (governed by the volume change associated with HS-LS or LS-HS transitions) and opposing anti-ferroelastic interactions (arising from the geometric restraints of the Kagome lattice) inhibit the formation of an ordered spin state. In pursuit of possible emergent spin ice behaviour, temperature and magnetic field dependent neutron scattering experiments were performed with the aim of identifying pinch points in magnetic diffuse scattering. Coupled with this, computational modelling of the powder averaged magnetic diffuse scattering is used to aid in locating these features in experimental data. Further investigation into the complex nature of these kagome structures may lead to the direct experimental observation of a spin ice in a 3-dimensional framework system.

## Deuteration of cholesterol for neutron applications

Marina Cagnes<sup>1</sup> ; Rob Russell<sup>1</sup> ; Carl Recsei<sup>2</sup> ; Tamim Darwish<sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> ANSTO - National Deuteration Facility

**Corresponding Author(s):** marinac@ansto.gov.au

Cholesterol is an essential component in animal cell membranes and a feature in lipid nanoparticle technologies. The National Deuteration Facility (NDF) at the Australian Nuclear Science and Technology Organisation (ANSTO) has recently experienced increased interest in access to deuterated cholesterol for neutron studies of biological systems, and lipid nanoparticles as drug and gene delivery vehicles.

The NDF has a reliable and robust method to produce deuterated cholesterol from bioengineered yeast in high purified yield. Different levels of deuteration are also possible through adjustment of growth media, and so can be tuned according to the application.

## Understanding and controlling the formation of photonic crystals from polydisperse colloidal systems

**Author(s):** Katherine Chea<sup>1</sup>

**Co-author(s):** Jitendra Mata <sup>2</sup> ; Philipp Reineck <sup>3</sup> ; Gary Bryant <sup>4</sup>

<sup>1</sup> RMIT University

<sup>2</sup> ANSTO

<sup>3</sup> ARC Centre of Excellence for Nanoscale BioPhotonics, RMIT University

<sup>4</sup> Centre for Molecular and Nanoscale Physics, School of Applied Sciences, RMIT University

**Corresponding Author(s):** s3542118@student.rmit.edu.au

The fundamentals of crystallisation and glass formation are not yet fully understood. Colloidal suspensions have been shown to be promising model systems for understanding these processes. As colloidal motion is Brownian, rather than ballistic, kinetics and dynamics can be studied in real-time. It is well documented that colloidal suspensions can “successfully crystallise” when the particles in the system have sufficiently low polydispersity.[1,2] If a system is highly polydisperse, this will hinder the solidification process.

Nanodiamonds are a topic of interest in many material studies due to their variety, and unique mechanical and optical properties.[3,4] Detonation nanodiamonds (DNDs) are of particular interest due to their unique fabrication process. Due to the detonation synthesis method, the particles are small (several nm) and faceted, but in solution self-assemble into highly irregular fractal shapes.[5] Despite this high polydispersity, when centrifuged, these types of DNDs can produce iridescent colours which are reminiscent of photonic crystals – this is highly surprising given the highly irregular structures of these materials. This phenomenon was first discovered by Grichko et al.,[5] however, the mechanism behind this process is still unknown. With a combination of lab techniques and experiments at the Australian Synchrotron and the Australian Centre for Neutron Scattering, we will systematically investigate these nanodiamond photonic crystals, and examine their structure and formation kinetics. We recently conducted experiments for SANS and USANS at ANSTO and investigated the structure of nanodiamonds to better characterise the structure of the nanoparticles, in particular the particle surface (non-diamond carbon plus functionalised layer). The DND particles were probed at three different contrasts to define the structures of the individual particles as well as their conglomerates.

44

## Deuterium labelling at the National Deuteration Facility: Updates on Demand and Supply

Tamim Darwish<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** tamim.darwish@ansto.gov.au

The use of deuterated molecules in neutron scattering experiments for investigating the relationship between molecular structure and function expands the range and complexity of science that can be conducted at reactor and spallation-source neutron facilities. There have been increasing global demand and initiatives in the field of molecular deuteration in the recent years; however, the complexity of the required molecules for new experiments has also increased. This has limited the experiments that can be performed and formed a bottle-neck for advancing the applications of neutron scattering.

In this paper we will discuss the recent advancements and the impact of deuteration on the research outcomes achieved by using bespoke deuterated molecules produced by the National Deuteration Facility. Recent high-impact case studies will be presented which reveal the exciting and diverse characterisation studies which are now available for the neutron research community. We will describe the synthesis and application of new deuterated molecules which are unavailable from commercial sources, such as deuterated cholesterol, proteins, phospholipids with deuterated oleic and linoleic chains, detergents for membrane proteins, and deuterated ionic liquids and metal-organic frameworks (MOFs) precursors. Such molecules were used to investigate complex nanoscale systems in the fields of structural biology, biotechnology and molecular electronics and storage using neutron scattering techniques.

## Using a computer game engine to teach neutron reflectometry alignment

Cortie David <sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** dcr@ansto.gov.au

Neutron reflectometry is a technique that probes the structure of thin films with nanoscale thickness. To produce an accurate reflectometry measurement, the sample must first be carefully aligned. This requires positioning the sample within 10 micrometres of its optimum position in the beam and ensuring the sample angle is aligned with a precision of at least 0.01 degrees. In practice, this is achieved using motorised translation and tilt stages, controlled using an iterative procedure of position and angle scans. Many users find the initial alignment process challenging.

In this poster, I will discuss a browser/Android app that has been developed to help teach users the process of alignment. The goal of this app is to build user confidence ahead of neutron reflectometry experiments. The app also covers some other useful skills including using the Swiss Instrument

Command System (SICS) and the procedure for mounting/dismounting samples including the basic radiation surveying step. The app covers the alignment protocol for both the Spatz and the Platypus reflectometers available at the ACNS.

I will discuss two different free game engines that can be used for rapidly developing this type of simulation-game, and show how the source code can be adapted to demonstrate different virtual neutron/X-ray instruments and techniques.

## **Solution structure characterisation of the complex of ubiquitin and its conjugating enzyme E2 by deuteration and small angle neutron scattering.**

Zuzanna Pietras<sup>1</sup> ; Anthony Duff<sup>2</sup> ; Vivian Morad<sup>1</sup> ; Kathleen Wood<sup>3</sup> ; Cy Jeffries<sup>4</sup> ; Sunnerhagen Maria<sup>1</sup>

<sup>1</sup> *Linköping University*

<sup>2</sup> *ANSTO*

<sup>3</sup> *Australian Nuclear Science and Technology Organisation*

<sup>4</sup> *European Molecular Biology Laboratory (EMBL) Hamburg Outstation*

**Corresponding Author(s):** anthony.duff@ansto.gov.au

This structural study exploits the possibility to use modular protein deuteration to facilitate the study of ubiquitin signalling, transfer, and modification. A protein conjugation reaction is used to combine the protonated E2 enzyme with deuterated ubiquitin for small angle neutron scattering with neutron contrast variation. The combined biomolecules stay as a monodisperse system during data collection in both protonated and deuterated buffers indicating long stability of the E2~Ub conjugate. With multiphase *ab initio* shape restoration and rigid body modelling we reconstructed the shape of a E2~Ub conjugated complex. Solution x-ray and neutron scattering data for this E2~Ub conjugate in the absence of E3 jointly indicate an ensemble of open and backbent states in solution, with a preference for the latter in solution. The approach of combining protonated and labelled proteins can be used for solution studies to assess localization and movement of ubiquitin and could be widely applied to modular ubiquitinated systems in general.

## **KOALA decommissioned October 2022 what has been achieved? and what remains to be done KOALA2 implementation under- way**

Alison Edwards<sup>1</sup> ; Ross Piltz<sup>1</sup>

<sup>1</sup> ACNS, ANSTO

**Corresponding Author(s):** alisonedwar@gmail.com

KOALA entered the Bragg Institute (now ACNS) user program in 2009 with the first chemical crystallography publication appearing in 2010. Since then 82 papers have appeared (56 chemical-crystallography).

This is the first time single-crystal neutron diffractometer output has been dominated by publications in chemical-crystallography. By the time all KOALA output appears this balance may shift even further. In the context of chemical crystallography, the major achievement with KOALA has been that the single-crystal neutron diffraction experiments and results have been obtained in time for them to be included in the high profile and high impact publications. A literature survey 2009 revealed that the earlier instruments had only rarely produced structures which were reported with the important chemistry for which the determinations were made, appearing years later in stand-alone crystallographic papers which were disconnected from the high-profile work and rarely cited. The stated aspirational aim of the Bragg Institute was to match the world leading neutron facilities for impact of publication and an initial target to achieve an average JIF for papers of 3. With the outstanding proposals that our community has made and our significant achievements in data reduction and analysis KOALA became sufficiently successful that it will now be the first of the initial Bragg Institute instruments to be renewed.

KOALA was the only instrument purchased entire from a “supplier” and the discipline of standardised motion control, electronics etc was not applied. This has rendered the original instrument obsolete and the achievements of our community have been recognised with the building of KOALA2 which will be introduced in this presentation.

2

## Strengthening Oxygen Lattice to Achieve Better-Performance Cobalt- free Li-Rich Layered Oxide Cathodes

Yameng Fan<sup>None</sup> ; Wei Kong Pang<sup>1</sup> ; Qiong Cai<sup>2</sup> ; Zaiping Guo<sup>3</sup>

<sup>1</sup> *University of Wollongong*

<sup>2</sup> *University of Surrey*

<sup>3</sup> *University of Adelaide*

**Corresponding Author(s):** yf645@uowmail.edu.au

Li-rich layered oxides are one of the most promising cathode candidates for the next-generation high-energy-density lithium-ion batteries. However, their real-world application is hindered by dramatic capacity fading and voltage decay on cycling. This work comprehensively studies the mechanistic behaviour of cobalt-free  $\text{Li}_{1.2}\text{Ni}_{0.2}\text{Mn}_{0.6}\text{O}_2$  and demonstrates the positive impact of Ru introduction for suppressing voltage decay and improving cycling performance. A mechanistic transition from the monoclinic to the hexagonal behaviour is found for the structural evolution of  $\text{Li}_{1.2}\text{Ni}_{0.2}\text{Mn}_{0.6}\text{O}_2$ , via in operando synchrotron-based X-ray powder diffraction. The enhancement mechanism of Ru doping is completely understood using Neutron-based pair distribution function analysis, neutron powder diffraction, synchrotron-based near-edge X-ray absorption fine structure and X-ray absorption characterizations. The Ru doping improves the structural reversibility in the first cycle and effectively restrains structural degradation during cycling by stabilizing oxygen redox and reducing Mn reduction, thus enabling high structural stability, an extraordinarily stable voltage (decay rate < 0.45 mV per cycle), and a high capacity-retention rate during long-term cycling. The fundamental understanding of the structure-function relationship of  $\text{Li}_{1.2}\text{Ni}_{0.2}\text{Mn}_{0.6}\text{O}_2$  sheds light on the selective doping strategy and rational materials design for better-performance Li-rich layered oxides, which is extendable to other types of electrodes for use in metal-ion batteries.



## Diffuse Scattering from a Martensitic Fe-Pd Alloy

Trevor Finlayson<sup>1</sup> ; Kyle Portwin<sup>2</sup> ; Kirrily Rule<sup>3</sup> ; David Cortie<sup>3</sup> ; Garry McIntyre<sup>4</sup>

<sup>1</sup> *University of Melbourne* <sup>2</sup> *University of Wollongong* <sup>3</sup> *ANSTO*

<sup>4</sup> *Australian Nuclear Science and Technology Organisation*

**Corresponding Author(s):** [trevorf@unimelb.edu.au](mailto:trevorf@unimelb.edu.au)

Fe-30at%Pd exhibits two martensitic transformations on being cooled from room temperature to 100 K, attributed to phonon softening. A preliminary study of a large single crystal of this composition on the Koala neutron Laue diffractometer at the OPAL reactor, not only showed evidence for these transformations but also revealed interesting and unexpected satellite reflections around certain Bragg reflections.

In a subsequent experiment at the Sika triple-axis spectrometer these satellite reflections were shown to involve elastic scattering to within 1 meV and the propagation vector around the (200) reflection of 0.180, [g0.186, [g0.034. During a parallel experiment to the Sika one, an ideally small piece of the crystal, electro-discharge machined from the large one, was studied on Koala but the interesting satellites found for the large crystal were not present. As a result, in a further experiment on the large crystal at Koala, completed in early 2021, diffraction patterns were collected with the aim of surveying the whole of the large crystal, particularly in the vicinity of the edge from which the ideally small crystal piece had been extracted. Each of these latter diffraction patterns showed the satellite reflections, an observation which raises the question as to why electro-discharge machining has affected the microstructural state of the large crystal.

It is now proposed to undertake further research at the Taipan triple-axis spectrometer using polarization analysis for one experiment and an applied magnetic field for the second, with the aim of solving the microstructural origin of the satellite reflections.

## Thermodynamics and local environment in liquid gallium under static magnetic fields

**Author(s):** Rong Fu<sup>1</sup>

**Co-author(s):** Richard Mole<sup>2</sup>; Dehong Yu<sup>2</sup>; Danica Solina<sup>1</sup>; Zhongming Ren<sup>3</sup>; Michael Cortie<sup>1</sup>

<sup>1</sup> *University of Technology Sydney*

<sup>2</sup> *Australian Nuclear Science and Technology Organisation*

<sup>3</sup> *Shanghai University*

**Corresponding Author(s):** rong.fu-3@student.uts.edu.au

Gallium is a fascinating element that melts as liquid metal at around room temperature ( $T_m = 302.9$  K) and keeps the liquid state till supercooled to 270 K, which endows it with complex solid and liquid characteristics. Its extraordinary physicochemical properties have resulted in gallium-based materials being applied in many fields and have attracted significant research attention. Unlike the diamagnetic in its solid state, the liquid gallium shows a slight paramagnetic attribute. Our research aims to reveal the effects of static magnetic fields (SMF) on liquid gallium on atomic scales. The study will provide the principle support for future liquid gallium-based materials applications under magnetic fields. We performed time-of-flight neutron scattering spectroscopy (Pelican, ANSTO), utilising a superconducting magnet, to study the atomic diffusion behaviours and local order profiles of liquid gallium (320 K) under SMF (0 – 4 T). The inelastic neutron scattering results are cross-validated and consistent with our previous high-energy X-ray diffraction experiments (under 0.2 T SMF). Those results of experiments and simulations indicate that SMF will influence atomic diffusion and drive short-range orders to form lower coordination numbers in local clusters.

### References:

1. Woo, M. Liquid metal renaissance points to wearables, soft robots, and new materials. *Proc. Natl. Acad. Sci. U. S. A.* 117, 5088–5091 (2020).
2. Pankey, T. Anisotropy of the Magnetic Susceptibility of Gallium. *J. Appl. Phys.* 31, 1802–1804 (1960).

## ACNS – Scientific Computing Services

Pablo Galaviz<sup>1</sup>

<sup>1</sup> *Australian Nuclear Science and Technology Organisation*

**Corresponding Author(s):** galavizp@ansto.gov.au

The Scientific Computing team supports researchers by performing numerical simulations that complement experimental research at the Australian Centre for Neutron Scattering. In particular, we use state-of-the-art software to perform computational quantum mechanical modelling, molecular dynamics simulations, lattice dynamics calculation, data analysis and visualisations.

In this poster, I will present the Scientific Computing Support service for the ACNS experiments. In particular, I will describe the techniques and give an overview of the software and hardware available for our researchers and users.

## Status, statistics, and recent research highlights from Echidna

James Hester<sup>1</sup>; Chin-Wei Wang<sup>2</sup>; Max Avdeev<sup>3</sup> <sup>1</sup> ANSTO

<sup>2</sup> NSRRC

<sup>3</sup> *Australian Nuclear Science and Technology Organisation, Australian Centre for Neutron Scattering*

**Corresponding Author(s):** jxh@ansto.gov.au

The Echidna high-resolution powder diffractometer remains a reliable and productive ACNS instrument contributing annually to about 50 published studies done on a wide range of topics, from magnetic, energy and planetary materials to cultural heritage and additive manufacturing. We will discuss how Echidna has recovered from COVID-19 impacts, latest and planned developments, user programme statistics, and recent research highlights.

19

## Interrogation of the mechanism of Li-mediated ammonia electro-synthesis by in situ neutron reflectometry

Rebecca Hodgetts<sup>1</sup> ; Callum Weir-Lavelle<sup>None</sup> ; Hoang-Long Du<sup>1</sup> ; Andrew Nelson<sup>2</sup> ; Alexandr Simonov<sup>1</sup>

<sup>1</sup> *Monash University*

<sup>2</sup> *ANSTO*

**Corresponding Author(s):** beck.hodgetts@monash.edu

To truly harness renewable energy, it is imperative we solve the issue of intermittent availability. Excess renewable energy can be stored as carbon free chemical fuels such as H<sub>2</sub> and NH<sub>3</sub>. These energy dense battery alternatives offer the ability to transport renewable energy off site, without reliance on an electrical grid. Currently NH<sub>3</sub> is primarily produced for implementation as a fertilizer via the anthropogenically expensive Haber Bosch process. To realise its use as a chemical fuel a sustainable production method is required, such as electrochemical reduction of N<sub>2</sub> into NH<sub>3</sub>. Currently, the only electrochemical process able to achieve this is the lithium mediated nitrogen reduction reaction (Li-NRR).<sup>1</sup> At Monash, we have developed Li-NRR methods capable of achieving a world leading 100% faradaic efficiency.<sup>2,3</sup> We have now turned our sights toward decreasing the energetic demands and increasing the overall sustainability of the process. This requires intelligent catalyst and electrolyte design, both of which can be facilitated by advancing our knowledge of the solid electrolyte interface (SEI). Blair et al. utilised in situ neutron reflectometry (NR) in an attempt to prove the state of the electrode during the Li-NRR but failed to obtain meaningful results as this work produced no ammonia.<sup>4</sup> We are in the process of using NR, combined with our insights from the development of highly efficient Li-NRR to describe the mechanism occurring at the electrode interface, and define the SEI environment responsible for high faradaic efficiency.

81

## Reflecting Neutrons with Platypus

Andrew Nelson<sup>1</sup> ; Anton Le Brun<sup>1</sup> ; Tzu-Yen (Ian) Huang<sup>2</sup> ; David Cortie<sup>1</sup> ; Stephen Holt<sup>3</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Centre for Neutron Scattering (ACNS) /Australian Nuclear Science and Technology Organisation (ANSTO)

<sup>3</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** sph@ansto.gov.au

PLATYPUS is the initial neutron reflectometer at the Australian Centre for Neutron Scattering with a capability to study surfaces and interface systems with applications from biomolecules, soft matter through to magnetic thin films [1-3]. There have been a number of significant improvements to both the instrument and data reduction and treatment software [4] over the last two years. On the hardware front the original detector has been replaced [5] enabling higher count rate capabilities, greater detection efficiency at shorter wavelengths and significantly lower background. The slits which define the neutron beam have been replaced with upgraded positioning mechanisms enabling greater flexibility in experimental setup. Most recently new slit blades have been installed resulting in a substantial reduction in instrument background. These changes have significantly enhanced the instrument performance with improved reproducibility.

[1] M. James et al., J. Neutron Research 14, 91 - 108 (2006)

[2] M. James et al., Nuclear Inst. and Methods in Physics Research A, 632, 112 - 123 (2011)

[3] T. Saerbeck et al., Rev. Sci. Instrum. 83, 081301 (2012)

[4] A. Nelson et al., J. Appl. Crystallography, 52, 193 - 200 (2019)

[5] L. Abuel et al., Journal of Neutron Research, 23(1), 53 – 67, (2021).

## Revealing composition and conformation of liposomes using integrated methods of HPLC/AF4, UV-Vis absorption, Refractive Index, MALLS, DLS, and SAXS-WAXS

**Author(s):** TING-WEI HSU<sup>None</sup> ; Kuei-Fen Liao<sup>None</sup> ; Yi-Qi Yeh<sup>None</sup> ; Orion Shih<sup>None</sup>

**Co-author(s):** U-Ser Jeng

**Corresponding Author(s):** hsu.tingwei@nsrrc.org.tw

Liposomes are increasingly better developed as efficient drug carriers. Structural characterization of the functional liposomes with and without drug-uptake and the consequent drug-transport and conditional drug-delivery, is of interest in biomedical applications. Here, we report an established combined methods using high-performance liquid chromatography (HPLC), asymmetric flow field-flow fractionation (AF4), UV-Vis absorption, refractive index (RI), multi-angle laser light scattering (MALLS), dynamic light scattering (DLS), and small- and wide-angle X-ray scattering for structural characterization of liposome solutions. We demonstrate an example of using the integrated system to successfully determine hydrodynamic radius and its distribution, molecular mass, lipid aggregation number, of a model liposome system of unilamellar vesicles (ULV). The radius of gyration  $R_g$  of 50 nm, hydrodynamic radius  $R_h$  of 50 nm, bilayer thickness, and lipid aggregation number of the ULV, with and without drug molecule loading, are determined using simultaneous small- and wide- angle X-ray scattering, incorporated with HPLC/UV-vis/RI, at the high-flux 13A BioSAXS undulator beamline of the 3.0 GeV Taiwan Photon Source. Moreover, a chain-chain packing peak of the ULV bilayers could be observed at  $q = 1.488 \text{ \AA}^{-1}$  ( $d = 4.28 \text{ \AA}$ ); reversible changes of the peak position and peak broadening with temperatures between 20 – 50C, providing a direct evidence of the correlation

of the lipid chain-chain packing with the commonly observed gel-ripple-fluid phase transitions of multilamellar vesicles.

82

## Reflecting Neutrons with Spatz

Anton Le Brun<sup>1</sup> ; Tzu-Yen (Ian) Huang<sup>2</sup> ; Stephen Holt<sup>3</sup> ; Andrew Nelson<sup>1</sup> ; David Cortie<sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Centre for Neutron Scattering (ACNS) /Australian Nuclear Science and Technology Organisation (ANSTO)

<sup>3</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** tzuyenh@ansto.gov.au

Spatz is the newest reflectometer at the Neutron Beam Facility of the OPAL Research Reactor. It has been in the ACNS User Program since November 2020 and has completed a number of experiments. Spatz operates using the time-of-flight principle and has a vertical sample geometry (horizontal scattering geometry). A wide variety of sample environments can be used on the instrument including solid-liquid cells and atmospheric chambers and heating stages. This presentation highlights the recent advances with Spatz including instrument developments and scientific highlights.

50

## Thermal Treatment on Vertical Morphology of PffBT4T-2OD: ITIC Non-fullerene Bulk Heterojunction Thin Films

Tzu-Yen (Ian) Huang<sup>1</sup><sup>1</sup> *National Synchrotron Radiation Research Center***Corresponding Author(s):** [huang.ty@nsrrc.org.tw](mailto:huang.ty@nsrrc.org.tw)

Solution-processable organic solar cells are extensively attractive in academic and industrial fields with the advantages of roll-to-roll processing and flexible and lightweight large-area devices. Bulk-heterojunction (BHJ) is a device architecture comprising electron donors and acceptors in the mix- tures. The donor-acceptor mixed phases in the BHJ morphology aid in dissociating the photogen- erated excitons and transporting the charges to the respective electrodes through the individual phase segregation. Therefore, optimizing BHJ nanomorphology for efficient exciton dissociation and charge extraction highly determines the device performance. Neutron reflectivity is conducive to probing the vertical morphology in a blend film. In this work, PffBT4T-2OD and ITIC are used as donor and acceptor materials in a BHJ layer. The study aims to (1) profile the vertical distribution of donor and acceptor phases in the blend film. Reveal the effect of donor-acceptor composition and solvents on the morphology change of the BHJ layer. (2) understand the changes in vertical morphology through thermal annealing. The elevated temperature possibly initiated the preferred molecular interaction to generate a morphology change in the BHJ layer. These results will com- plement the other characterization techniques, such as AFM, GIWAXS, and molecular dynamics simulation, assisting in developing high-efficient non-fullerene organic solar cells.



## Residual stress in multilayer laser cladding depositions on light rail components

**Author(s):** Olivia Kendall<sup>1</sup>

**Co-author(s):** Ralph Abrahams<sup>1</sup>; Mark Reid<sup>2</sup>; Anna Paradowska<sup>2</sup>; Cong Qiu<sup>3</sup>; Peter Mutton<sup>3</sup>; Wenyi Yan

<sup>1</sup>

<sup>1</sup> *Monash University*

<sup>2</sup> *ANSTO*

<sup>3</sup> *Monash Institute of Railway Technology*

**Corresponding Author(s):** olivia.kendall@monash.edu

A shift towards sustainable practices places an increasing demand on Australia's public transport networks. This results in growing rates of rail wear and fatigue due to high passenger loads, increasing operation speeds and service frequency. Light rail is particularly susceptible to these damage modes as components such as switches are manufactured from lower steel grades. As rail replacement procedures are both expensive and disruptive, new maintenance techniques are required to efficiently recondition light rail components.

Laser cladding is an additive manufacturing-based repair strategy which utilises a high energy laser to melt a metallic powder at the rail surface to form a metallurgically bonded coating. To rebuild worn rail profiles, multiple layers of cladding are required which exposes the underlying substrate to cycles of melting and solidification. This alters the microstructure with each successive layer, resulting in internal stress which may increase the susceptibility to fatigue failure. Accurately measuring the residual stresses after multi-layer laser cladding is critical to ensure repairs are safe for railway operation.

To determine the stress generation after multi-layer depositions, double-layer laser cladding has been carried out on 600 mm sections of ex-service tram rail using Stellite 21. The triaxial residual stresses were measured on the Kowari strain scanner using through thickness line scans that traverse the cladding, heat affected zone and rail substrate. Comparison of these results with single depositions will provide information on the tempering effects of repeated cladding cycles and how this may affect the rail lifetime. These findings will accompany microstructural and mechanical property analysis to determine the optimal cladding parameters for light rail repair to be implemented by the railway industry.

58

## EMU cold-neutron backscattering spectrometer at ACNS, ANSTO

Alice Klapproth<sup>1</sup>; Nicolas de Souza<sup>2</sup> <sup>1</sup> ANSTO

<sup>2</sup> ANSTO - Australian Centre for Neutron Scattering

**Corresponding Author(s):** akl@ansto.gov.au

EMU is the high-resolution neutron spectrometer installed at the OPAL reactor, ANSTO, which delivers 1  $\mu\text{eV}$  FWHM energy transfer resolution for an accessible  $\pm 31 \mu\text{eV}$  energy transfer range. The spectral resolution is achieved by neutron backscattering from Si (111) crystals on the primary and secondary flight paths, allowing up to 1.95  $\text{\AA}^{-1}$  momentum transfer range. The spectrometer is well suited for quasi-elastic and inelastic neutron scattering studies, notably in the field of soft-condensed matter including biophysics and polymer science, chemistry and materials science, and geosciences. Most experiments are carried out with standard cryofurnaces (2 to 800 K temperature range). Spectrometer beam-time access is merit-based, thus welcoming as well experiments in other materials research areas, and including experiments that may require e.g. other ancillary equipment such as existing controlled-gas delivery, and potentially pressure, applied field set-ups, etc. Examples of the spectrometer capabilities are shown through select case studies.

8

## Experimental and numerical investigation of fracture in welded connections

Xiaofan Liu<sup>None</sup> ; Kim Rasmussen<sup>None</sup> ; Anna Paradowska<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** xliu9740@uni.sydney.edu.au

The steel structures are built from beams and columns that may fail in a steel frame because of local yielding, buckling or fracture, and our project focuses on one of the most important failure modes in the structural analysis, the fracture in welded connections. The rapid heating and uneven cooling of different parts during the welding process will cause significant residual stresses. And the high temperature also locally changes the microstructure of the base metal and leads to altering of the mechanical properties in the neighbouring areas of the weld and the heat-affected zone. These welding-related properties, such as tensile residual stresses and change in mechanical properties in and around welds, play a significant role in the behaviour of steel connections and need to be characterised and optimised to minimise their effects on welds fracture.

Triaxial residual stress generated by different types of welds are systematically investigated through the neutron diffraction approach using the strain scanner Kowari at ANSTO. The detailed 3D distribution of the residual stress in the welded cruciform specimens and end-plate connection provide a more comprehensive understanding the complex steel connections. Based on these measurements, the fracture behaviour of welded connections will be analysed, and the effect of welding-related properties will be discussed.

## Multiscale structure parameters affecting phase transitions in PbZrO<sub>3</sub>-based antiferroelectric ceramics

Teng Lu<sup>1</sup>

<sup>1</sup> *The Australian National University*

**Corresponding Author(s):** [teng.lu@anu.edu.au](mailto:teng.lu@anu.edu.au)

Antiferroelectric (AFE) materials are considered as promising candidates for energy conversion and storage devices. The main origin of these potential applications arises from the distinctive structural transition induced by external stimuli such as electric-field (E-field), temperature and mechanical force. Thus, it becomes pressing to unveil the structure parameters affecting the critical fields and phase transitions. This study systematically investigates the structural and crystallographic texture change as a function of the E-field and temperature in the prototype PbZrO<sub>3</sub>-based AFE materials. It is found that in addition to the crystal structure parameters such as antiparallel atomic displacements and octahedral tilting, the microscopic crystallographic texture can also influence the critical E-field triggering the AFE-ferroelectric (FE) phase transition. The degree of the crystallographic texture can be adjusted via the external E-field and temperatures, which directly modifies the energy barrier between the AFE and FE phases. It is found that the aligned state presents a lower critical E-field compared with that of the random state. Our results demonstrate that multiscale structure

parameters can be used to tune the properties of the AFE materials. Moreover, these parameters can be not only modified by the chemical compositions and synthesis conditions but also controlled by the history of the applied E-field and temperatures, which introduces a new strategy for improving the performances of AFE materials.

61

## A 3-D Reconstruction of neutron activation in samples irradiated at DINGO

**Author(s):** Sherryn MacLeod<sup>None</sup>

**Co-author(s):** Joseph Bevitt <sup>1</sup> ; Mitra Safavi-Naeini <sup>1</sup> ; Andrew Chacon ; David Zahra

<sup>1</sup> ANSTO

**Corresponding Author(s):** sherryn.j.macleod@student.uts.edu.au

Non-destructively characterising the interior elemental composition of bulk samples (larger than a few hundred  $\mu\text{m}$ ) is essential across many fields (e.g. archaeometry, palaeontology, mining, etc.) for obtaining a holistic picture of an object and its context. Traditional neutron activation analysis (NAA) techniques are utilised to identify elemental distributions within bulk samples, however, these techniques do not yield the 3-D spatial information needed to determine where in the object these elements originate. Alternatively, advanced imaging techniques such X-ray and neutron tomography yield 3-D structural information, but the tomographic reconstructions cannot often be accurately extrapolated to yield internal elemental distributions.

To address this issue, a novel method that combines neutron scattering and medical imaging techniques has been proposed. Using ANSTO's thermal-neutron imaging instrument (DINGO), samples are irradiated with thermal neutrons, during which, a fraction of the nuclei within these samples will become activated via neutron capture. Similarly to NAA, as the resulting radionuclides decay, the characteristic energies of emitted gamma photons can be measured to uniquely identify the isotopes created. By performing single-photon emission computed tomography (SPECT) of the neutron-irradiated samples over an extended period, the spatial distribution of elements, via their radioisotopes, can be determined. To validate this method, 3-D reconstructions of Cu-64 in copper samples have been achieved, with reconstructions of other elemental samples pending. Given these results, post-neutron-tomography SPECT imaging has the potential to produce 3-D isotopic reconstructions of bulk objects which can be further combined with existing tomography data to create rich multidimensional datasets about a sample.

1

## Recent Achievements in Neutron Backscattering

**Author(s):** Andreas Magerl<sup>1</sup>

**Co-author(s):** Markus Appel<sup>2</sup> ; Berhard Frick<sup>2</sup>

<sup>1</sup> *University Erlangen-Nürnberg*

<sup>2</sup> *Institut Laue Langevin*

**Corresponding Author(s):** andreas.magerl@fau.de

Crystal spectrometers such as IN16B at the Institut Laue-Langevin in Grenoble, France, operating in backscattering provide high energy resolution down to sub-micro-eV. While the spectrometer IN16B has been serving its international user community for about a decade, we continuously strive to extend the capabilities of these spectrometers well beyond today's limits. In the presentation, we focus on two recent major achievements.

A first upgrade of IN16B aimed at the installation of a ToF opportunity into the primary spectrometer necessitating a very fast chopper system. This initiated the fabrication of novel chopper disks made from oriented carbon fibers. The resulting new BATS option (Backscattering And ToF Spectrometer) offering an energy transfer range enhanced by more than one order of magnitude has been brought into routine user recently. At present, we are installing a variable guide focusing element in the vicinity of the choppers which will enhance the neutron flux at the sample up to a factor of 6.

In addition, we have demonstrated the feasibility of a future ultra-high energy resolution backscattering spectrometer by replacing the Si 111 reflection generally used today by the GaAs 200 reflection featuring a significantly smaller Darwin width. The established energy resolution is 76 neV, one order of magnitude superior than available in standard backscattering setups.

42

## Neutron Polarisation Capabilities at ACNS

Andrew Manning<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** andrewm@ansto.gov.au

By controlling the spin of neutrons during scattering experiments, unique information about samples can be found that would not be available otherwise. Manipulating and filtering the neutron spin both

before and after its interaction with a sample allows not only more detail about magnetic structures to be found, but also enables coherent and incoherent scattering signals to be distinguished.

An overview of the neutron polarisation capabilities offered at ACNS will be summarised here, including details of the six neutron scattering instruments which are compatible with polarisation experiments, as well as some examples of the types of measurements which can be undertaken.

74

## How ionic liquid composition and structure affect micelle morphology

**Author(s):** Joshua Marlow<sup>1</sup>

**Co-author(s):** Kathleen Wood<sup>2</sup> ; Rob Atkin<sup>3</sup> ; Gregory Warr<sup>4</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Nuclear Science and Technology Organisation

<sup>3</sup> The University of Western Australia

<sup>4</sup> The University of Sydney

**Corresponding Author(s):** marlow206@gmail.com

A common method of making viscoelastic, wormlike micellar systems in water is to combine a cationic surfactant with a salt featuring a strongly bonding or hydrotropic counterion, such as sodium salicylate. Despite their inherent high ionic strength and evidence for cylindrical or wormlike micelles, viscoelastic micellar systems have yet to be reliably observed in ionic liquid solvents.

In this work, micellar structures of a series of alkyltrimethylammonium and alkylpyridinium salicylate surfactants were examined by small-angle neutron scattering (SANS) in the protic ionic liquids ethylammonium nitrate (EAN), ethanolanmonium nitrate (EtAN), ethanolanmonium formate (EtAF), their mixtures, and aqueous solutions.

Results reveal the conditions under which wormlike micelles form and elucidates how solvent structural features such as ionic strength, H-bond connectivity and the inherent liquid amphiphilic nanostructure affect micelle morphology. In turn, learning about these subtleties provides a greater understanding of how amphiphilic self-assembly occurs in neoteric solvents, allowing for more directed design of such systems for a variety of applications.



23

## Understanding nanoplastic toxicology using neutron scattering techniques.

Jitendra Mata<sup>1</sup> ; Shinji Kihara<sup>2</sup> ; Ingo Koeper<sup>3</sup> ; McGillivray Duncan<sup>4</sup>

<sup>1</sup> ANSTO

<sup>2</sup> University of Copenhagen

<sup>3</sup> Flinders University

<sup>4</sup> The University of Auckland

**Corresponding Author(s):** [jtm@ansto.gov.au](mailto:jtm@ansto.gov.au)

In nature, most plastics physically and chemically degrade to form minute particles on the micro- and nanometer scale. Multiple international agencies have recently raised environmental and health concerns regarding these micro and nano plastics, but there is insufficient knowledge of their properties to allow for an accurate risk assessment to be conducted and any risks managed. For this reason, research into the toxicity of nanoplastics has focused strongly on documenting their impacts on biological organisms. In this work we summarise the recent findings on the adverse effects on biological organisms and strategies which can be adopted to advance our understanding of nanoplastic properties and their toxicity. Identifying the chemical and biological bases behind the observed biological effects (such as in vitro cellular response) is a major challenge, due to the intricate nature of nanoparticle-biological molecule complexes and an unawareness of their interaction with other biological targets, particularly at interfacial level. An exemplary case includes protein corona formation and ecological molecule corona (eco-corona) for nanoplastics. We also highlight recent findings and importance of coronae formation and structure characterisation especially using neutron scattering techniques. Finally, we discuss the opportunities provided by model system approaches (model protein corona and lipid bilayer) to deepen the understanding of the above-mentioned perspectives and corroborate the findings from in vitro experiments.

## Kookaburra, the ultra-small-angle neutron scattering instrument at ANSTO: design and recent applications

Jitendra Mata<sup>1</sup>; Liliana de Campo<sup>1</sup>; Christine Rehm<sup>1</sup> <sup>1</sup> ANSTO

**Corresponding Author(s):** [jtm@ansto.gov.au](mailto:jtm@ansto.gov.au)

The double-crystal ultra-small-angle neutron scattering (USANS) diffractometer Kookaburra at ANSTO was made available for user experiments in 2014. Kookaburra allows the characterization of microstructures covering length scales in the range of 0.1–20  $\mu\text{m}$ . Use of the first- and second-order reflections coming off a doubly curved highly oriented mosaic pyrolytic graphite pre-monochromator at a fixed Bragg angle, in conjunction with two interchangeable pairs of Si(111) and Si(311) quintuple-reflection channel-cut crystals, permits operation of the instrument at two individual wavelengths, 4.74 and 2.37  $\text{\AA}$ . This unique feature among reactor based USANS instruments allows optimal accommodation of a broad range of samples, both weakly and strongly scattering, in one sample setup [1,2]. The versatility and capabilities of Kookaburra have already resulted in a number of research papers, including studies on hard matter systems like rocks and coal [3,4], as well as soft matter systems like hydrogels or milk [5,6]. This clearly demonstrates that this instrument has a major impact in the field of large-scale structure determination. Some of the recent examples will be presented here.

### References

- [1] Rehm, C. et al, *J. Appl. Cryst.*, 2013, 46 1699-1704.
- [2] Rehm, C. et al, *J. Appl. Cryst.*, 2018, 51, 1-8.
- [3] Blach, T. et al, *Journal of Coal Geology*, 2018, 186, 135-144.
- [4] Sakurovs, R. et al, *Energy & Fuels*, 2017, 31(1), 231-238.
- [5] Whittaker, J. et al, *Int. J. Biol. Macromol.*, 2018, 114, 998-1007.
- [6] Li, Z. et al, *Food Hydrocolloid*, 2018, 79, 170-178.

53

## Deuteration as a tool for structure determination of membrane proteins

**Author(s):** Michael Moir<sup>1</sup>

**Co-author(s):** Rao Yepuri<sup>2</sup> ; Tamim Darwish<sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** moirm@ansto.gov.au

Membrane proteins are important structures for cellular function. Around a third of all human proteins are membrane-bound, and they account for about a half of all drug targets.[1,2] Despite their obvious importance, determination of the structure of membrane proteins is still a significant challenge. This mainly pertains to the difficulty of preserving the native conformation of the protein once it has been removed from its endogenous environment. The National Deuteration Facility, ANSTO, has a large catalogue of specifically deuterated materials that are able to facilitate a suite of methods to obtain structural information about membrane proteins.[3] Deuteration allows for small-angle neutron scattering (SANS) of membrane proteins without contribution from contrast- matched membrane protein carrier systems: detergents, lipid nanodiscs and lipid mesophases.[4,5,6] To obtain satisfactory SANS signal-to-noise of the membrane protein structure, the detergents or

lipids are synthesised with deuteration levels such that they have the same neutron scattering length density as the surrounding aqueous buffer. Herein, we disclose an overview of the synthetic methods used to access important deuterated detergents and lipids and provide examples of their recent use in structural biology.

### References

1. K. Lundstrom, *Curr. Opin. Drug Discovery Dev.*, 7, 342 (2004).
2. R. F. Service, "Gently Does It" *Science*, 343, 1094, (2014).
3. <https://www.ansto.gov.au/our-facilities/national-deuteration-facility> 4. L. van't Hag; et al., 35(25) 8344, (2019).
5. S. R. Midtgaard; et al. *FEBS J.*, 285(2), 357-371, (2018).
6. S. Waldie; et al. *Front. Chem.*, 9, (2021).

32

## Supermirror focussing guide for Pelican

Richard Mole<sup>1</sup> ; Phillip Bentley<sup>2</sup> ; Scott Olsen<sup>1</sup> ; Dehong Yu<sup>3</sup>

<sup>1</sup> ANSTO

<sup>2</sup> European Spallation Source

<sup>3</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** richard.mole@ansto.gov.au

Pelican is a cold-neutron time-of-flight spectrometer at the Australian Centre for Neutron Scattering. It has applications in a diverse range of scientific disciplines. One fundamental limitation of nearly all neutron spectroscopy is the requirement for relatively large samples due to signals (and thus measurements) being flux limited. To address this we are designing a system of focusing supermirror neutron guides that will allow a factor of ten increase in the beam intensity at on a 10 mm x 10 mm beam spot at the sample position. In this contribution we will demonstrate the design concept and ray tracing simulations that demonstrate that this will be possible. We will also give an overview of the increased scientific capabilities that will be possible using this neutron optics upgrade, this includes but is not limited to small single crystal samples, use of high-pressure cells with small sample spaces and the measurement of difficult to synthesise samples.

34

## Neutron scattering measurements on rare earth single molecule magnets.

Richard Mole<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** richard.mole@ansto.gov.au

Single molecule magnets are a class of materials which show a magnetic bistability and hysteresis on a molecular level. Such properties have meant they are potential candidates for spintronics applications, data storage and as qubits. Inelastic neutron scattering has been shown to give unique information on these materials as it allows the ground state splitting to be probed directly. In recent years we have demonstrated that combined with *ab initio* calculations the structure property relationships can be understood. More recently it has been demonstrated that spin-phonon coupling can also be measured directly using this technique. Finally new sample environment has meant that it is possible to probe these effects in the presence of a static magnetic field. In this contribution I will give a summary of the work that has been completed on these fascinating materials at the ACNS.

33

## Recent highlights from the Pelican spectrometer

Richard Mole<sup>1</sup> ; Dehong Yu<sup>2</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** richard.mole@ansto.gov.au, dyu@ansto.gov.au

Pelican is a cold-neutron time-of-flight spectrometer at the Australian Centre for Neutron Scattering (ACNS). Pelican has been in operation since 2014 and has been used for a diverse range of applications, including single molecule magnets, barocaloric materials, solid oxide conductors for quantum magnets. In this contribution we will present some recent highlights from the Pelican spectrometer demonstrating the varied capabilities of the instrument.

72

## Neutron Diffraction at the start and end of the Nuclear Fuel Cycle

Brendan Kennedy<sup>1</sup> ; Zhaoming Zhang<sup>2</sup> ; Maria Nicholas<sup>1</sup>

<sup>1</sup> *The University of Sydney*

<sup>2</sup> *ANSTO*

**Corresponding Author(s):** mnic3813@uni.sydney.edu.au

Uranium oxides are the foundation of the nuclear fuel cycle, presenting as complex chemical species in both uranium ore concentrates, to phases of interest in the development of stable waste forms at the end of the nuclear fuel cycle. Australia is a major exporter of uranium and has a responsibility to contribute to the long-term management of nuclear materials. This requires an in-depth structural understanding of materials present in the nuclear fuel cycle, and how they respond to changes in the environment.

Two such examples of uranium oxides at the start and end of the nuclear fuel cycle are  $[\text{UO}_2(\eta^2\text{-O}_2)(\text{H}_2\text{O})_2]$  (metastudtite), and  $\text{CaUNb}_2\text{O}_8$ , a scheelite-type oxide.

The precise structure of metastudtite is controversial with low resolution structural studies supported by DFT calculations suggesting that the trans-uranyl group is not linear. Non-linear uranyl groups are uncommon, with a recent study using metastudtite sourced from the Beverley mine in Australia showing that the trans-uranyl groups are linear in conflict with the DFT study. We hope to resolve these issues using high resolution neutron diffraction to establish an accurate and precise structure of  $[\text{UO}_2(\eta^2\text{-O}_2)(\text{H}_2\text{O})_2]$  in a combined S-XRD+NPD study.

$\text{CaUNb}_2\text{O}_8$  is a rare example of a scheelite-type oxide containing  $\text{U}^{4+}$  on the 8-coordinate site. In situ variable temperature synchrotron X-ray powder diffraction confirmed a reversible phase transformation from fergusonite to scheelite. With our upcoming in situ neutron powder diffraction measurements, the nature of the fergusonite to scheelite transformation in  $\text{CaUNb}_2\text{O}_8$  will be revisited and the thermal stability of the scheelite explored.

88

## Experimental and Computational Studies of Sulfided NiMo Supported on Pillared Clay: Catalyst Activation and Guaiacol Adsorption Sites

Ferensa Oemry<sup>1</sup>; Indri Adilina<sup>1</sup>; Wahyu Tri Cahyanto<sup>2</sup>; Nino Rinaldi<sup>1</sup>; Fauzan Aulia<sup>1</sup>; Adam Jackson<sup>3</sup>; Stewart Parker<sup>4</sup>; Anna Kroner<sup>5</sup>; Elizabeth Shotton<sup>5</sup>

<sup>1</sup> National Research and Innovation Agency

<sup>2</sup> Soedirman University

<sup>3</sup> Scientific Computing Department, STFC Rutherford Appleton Laboratory

<sup>4</sup> ISIS Neutron and Muon Source, STFC Rutherford Appleton Laboratory

<sup>5</sup> Diamond Light Source Ltd, Diamond House, Harwell Science and Innovation Campus

**Corresponding Author(s):** ferensa102@gmail.com

We report on intermediate (oxysulfides) and sulfided structures of NiMo supported on aluminium pillared clay (Al-PILC) during the catalyst activation process and the preferred guaiacol adsorption sites on the sulfided catalyst. In situ X-ray absorption fine structure (XAFS) together with density functional theory (DFT) calculations confirm the existence of ill-defined suboxides (MoO<sub>x</sub>, NiO<sub>x</sub>) and the well-known subsulfides (Mo<sub>2</sub>S<sub>9</sub>, Ni<sub>3</sub>S<sub>2</sub>) at the first stage which, at a later stage in the process, transform into MoS<sub>2</sub> with oxygen-decorated Mo and Ni edges. The freshly sulfided NiMoS<sub>2</sub> catalyst under sulfiding agents is mainly terminated by Mo-edge surface with 50% sulfur coverage (Mo-S50) with a disordered Ni-edge surface that can be assigned as NiMoS (1010). When exposed to an inert atmosphere such as He gas, the Mo and Ni edges evolved partially into new structures of Mo and Ni edges with zero sulfur coverage, labelled as Mo-Bare and Ni-Bare. Guaiacol is often used as a model compound for lignin and a series of calculations of guaiacol on the structural edges of a sulfided NiMoS<sub>2</sub> catalyst show relatively good agreement between the observed and calculated inelastic neutron scattering (INS) spectra for Mo-S50, Ni-Bare, and NiMoS (1010) where guaiacol weakly chemisorbed via oxygen atom of OH group. The results also confirm that guaiacol is physisorbed on the basal plane of NiMoS<sub>2</sub> in a horizontal (flat-lying) configuration via van der Waals interaction at a separation of about 3.25 Å.



76

## Update on the progress of ACNS Industrial Liaison Office and future opportunities

Anna Paradowska<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** [anp@ansto.gov.au](mailto:anp@ansto.gov.au)

### Abstract

The instruments at ACNS have a unique non-destructive ability to assist academia and industry in the characterisation of the materials and improvements of the manufacturing processes. ACNS ILO versatile team has established a strong record in assisting Australian and international researchers and engineers across a wide range of projects. Over time, we have built a team with unique experience and technical expertise, which is now on offer to support industrial research and development.

This presentation will focus on the recent expansion of the team, showcase industry highlights and opportunities to further enhance the industry engagement. Our collaborative approach help industry find the competitive edge via neutrons and in consequence improve safety, efficiency, quality and often reduce the cost of materials or manufacturing process.

## Topologically stabilized spin configurations in rare- earth based systems using polarized neutron scattering

Amitesh Paul<sup>None</sup>

**Corresponding Author(s):** amitesh.paul@gtiit.edu.cn

Structural and magnetic correlations can be accessed by various neutron and x-ray scattering techniques at low angles. Topologically stabilized spin configurations like helices in the form of planar domain walls with magnetic functionalities in transition metal/rare-earth and rare-earth/rare-earth systems are readily investigated using polarized neutron reflectivity (PNR). Recently, using magnetization and susceptibility as a function of temperature along with thermo-remanent magnetization measurements we have confirmed the superspin-glass (SSG) type of behavior within the rare-earth/rare-earth systems of Dy/Tb, and also other transition-metal/rare-earth systems. Interestingly, a detailed analysis of the polarized neutron reflectometry profiles has established evidence of superimposed helical magnetic configurations within both rare-earth materials of Dy and Tb associated with spin-frustrated interfaces. Such coexistence of SSG and helical phases is due to the spin frustrated interdomain magnetic interaction as indicated by polarized off-specular neutron scattering. The quantized energy spectrum within finite magnetic chains results in stabilizing topologically protected configurations of helices. Since both materials are anisotropically hard and their respective helical and ferromagnetic ordering temperatures are also significantly different in bulk form, it was hardly expected for them to establish exchange-coupled helices. Thus, our work realizes a novel state of spin configuration even within such unusual candidates. Realization of such spin configurations opens up the opportunity for scientific and technological applications in increasing the energy density for all-spin-based systems and eventually controlling the chirality in such systems, proving an extra degree of freedom in spintronics.

COMMUNICATIONS PHYSICS | <https://doi.org/10.1038/s42005-019-0210-0>

39

## Structures of photocycle intermediates of the orange carotenoid protein studied by small angle scattering using partial deuteration

Jörg Pieper<sup>1</sup><sup>1</sup> *University of Tartu***Corresponding Author(s):** pieper@ut.ee

The orange carotenoid protein (OCP) plays a pivotal role in photoprotection in cyanobacterial photosynthesis. OCP undergoes significant structural changes upon illumination. The photoprotective function of OCP is terminated by complex formation with the fluorescence recovery protein (FRP). The individual steps of the OCP-FRP interaction are currently a matter of intensive research efforts. We used small-angle neutron scattering coupled in part with size exclusion chromatography to unravel the solution structures of two variants of OCP lacking the N-terminal extension (OCP- $\Delta$ NTE) and its complex formation with FRP. The dark-adapted, orange form OCP-O is compact and fully photoswitchable. Its complex with FRP consists of a monomeric OCP component, which closely resembles the compact structure expected for the OCP ground state. In contrast, the pink form OCP-P is mostly non-switchable. The latter pink OCP form appears to be characterized by a significant separation of the NTD and CTD protein domains. Therefore, OCP-P can be viewed as a prototypical model system for the active state of OCP. The dimeric structure of OCP-P is retained in its complex with FRP. Small-angle neutron scattering using partially deuterated OCP-FRP complexes reveals for the first time that FRP has to undergo significant structural changes upon complex formation with both OCP forms, a feature not visible in complementary small angle X-ray experiments. We conclude that both OCP-FRP structures determined resemble individual intermediate complex states of the OCP photocycle, one resembling the complex of the active form of OCP with FRP, while the other one is similar to a step in the back-conversion of OCP from the active state to the dark-adapted ground state.

54

## Diverse Deuterated Lipids for Neutron Applications

Carl Recsei<sup>1</sup>

<sup>1</sup> ANSTO - National Deuteration Facility

**Corresponding Author(s):** recseic@ansto.gov.au

Deuterated small molecules are an important tool in structure-function investigations using neutron scattering and diffraction techniques. Where the availability of deuterated small molecules is insufficient in terms of quantity or diversity a bottleneck is created which limits the advancement of neutron techniques.

We will discuss recent advancements in and the impact of deuteration upon the research outcomes achieved by using bespoke deuterated lipids produced by the National Deuteration Facility of the Australian Nuclear Science and Technology Organisation. We will describe the synthesis and application of new deuterated molecules which are unavailable from commercial sources, as well as the

challenges and opportunities associated with expanding the menu of deuterated lipids available for neutron applications.

89

## Recent upgrades to the Kowari strain scanner

Mark Reid<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** mark.reid@ansto.gov.au

This poster will highlight some recent upgrades to the Kowari residual strain scanner. These include, implementation of an oscillation system for the radial collimators on the detector, as well as improvements to the general motorisation of the detector. In addition the new ATOS5 GOM structured light scanner will also be described.

18

## The role of the solvent in specific ion effects: PNIPAM brushes in non-aqueous electrolytes

**Author(s):** Hayden Robertson<sup>None</sup>

**Co-author(s):** Isaac Gresham<sup>1</sup>; Andrew Nelson<sup>2</sup>; Stuart Prescott<sup>3</sup>; Grant Webber<sup>4</sup>; Erica Wanless<sup>5</sup>

<sup>1</sup> *University of Sydney*

<sup>2</sup> *ANSTO*

<sup>3</sup> *UNSW Chemical Engineering* <sup>4</sup> *The University of Newcastle* <sup>5</sup> *University of Newcastle*

**Corresponding Author(s):** hrobertson1@uon.edu.au

Stimulus-responsive polymers can uniquely alter their conformation as a function of external factors. When these polymers are densely tethered to a surface (forming a polymer brush), the conformational change can be used to modify interfacial properties. One such system is the thermoresponsive poly(N-isopropylacrylamide) (PNIPAM) brush, which undergoes a phase transition from well- to poorly-solvated over a broad temperature range, thereby profoundly changing the interaction of the surface with biological media (e.g., cellular adhesion, protein adsorption). The phase transition of polymer brushes can also be moderated by the inclusion of ions, where the change to higher or lower temperatures is dependent on the identity of the ion: specific ion effects (SIE).<sup>1</sup>

Natural environments are composed of complex mixtures of aqueous and non-aqueous electrolytes, which poses both a challenge and an opportunity for the deployment of responsive polymer systems. The challenge is that the behaviour of these polymers in complex solutions must be understood, the opportunity is that certain solution components may be used as additional stimuli. To probe the behaviour of the brush in these complex electrolytes, we investigate changes in the behaviour of a PNIPAM brush in mixed dimethyl sulfoxide/aqueous electrolytes using neutron reflectometry (NR). NR (Platypus) is the only technique capable of resolving the subtle yet detailed changes within the internal structure of the brush. However, significant advances in modelling NR data were required to deconvolute these subtle changes in brush structure (including describing the diffuse brush with interpolating polynomials);<sup>2</sup> unveiling the complex relationship between the solvent, solute (i.e., ions) and substrate (i.e., polymer brush).

<sup>1</sup>Gregory, Elliot, Robertson et al., 10.1039/D2CP00847E

<sup>2</sup>Gresham, Murdoch, Johnson, Robertson and et al., 10.1107/s160057672100251x

20

## refnx + refellips: Analysing neutron/X-ray/light scattering from surfaces in Python

Hayden Robertson<sup>None</sup> ; Isaac Gresham<sup>1</sup> ; Stuart Prescott<sup>2</sup> ; Erica Wanless<sup>3</sup> ; Grant Webber<sup>4</sup> ; Andrew Nelson<sup>5</sup>

<sup>1</sup> University of Sydney

<sup>2</sup> UNSW Chemical Engineering

<sup>3</sup> University of Newcastle

<sup>4</sup> The University of Newcastle

<sup>5</sup> ANSTO

**Corresponding Author(s):** hrobertson1@uon.edu.au

At ACNS we are fortunate to have a wide variety of tools for characterising interfacial structures using neutrons, X-rays and light, via neutron and X-ray reflectometry (NR + XRR), and ellipsometry. The complementarity of these techniques improves understanding of complex interfaces as each of the techniques are sensitive to different aspects of the system. For example, NR and XRR are very sensitive to the thickness of a polymer film, which can then be used as a constraint when modelling

its optical dielectric function from ellipsometry data.

Unfortunately many proprietary ellipsometry analysis packages are typically tied to specific hard-ware, not designed for reproducible research, and can't be combined with modelling packages for other techniques.

Here we present a new package, *refellips*, an open-source package for the analysis of ellipsometry data, that is designed to address all these issues. Moreover, *refellips* is integrated with the neutron and X-ray reflectometry analysis software, *refnx* (also developed at ACNS). This integration makes it possible to model share and co-refine neutron and X-ray reflectometry, and ellipsometry data, for the first time.

Here we outline the main points of *refellips*, how ellipsometry can be used to inform NR and XRR experimental design, and demonstrate its use in a corefinement process.

64

## Development of the yeast platform in the NDF for expanding the range of lipids available to researchers.

Rob Russell<sup>1</sup> ; Carl Recsei<sup>2</sup> ; Marina Cagnes<sup>None</sup> ; Tamim Darwish<sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> ANSTO - National Deuteration Facility

**Corresponding Author(s):** rar@ansto.gov.au

The expansion of biosynthetic capability of the NDF has provided a greater range of molecules for neutron and other research techniques. Yeast and other microbes have been selected for expression of deuterated sterols including cholesterol and campesterol, that have been used in neutron scattering investigations of SARS-CoV-2 infection and mRNA vaccine development.<sup>1,2</sup> We have recently formed a collaboration with the ARC Centre of Excellence in Synthetic Biology at Macquarie University to create new yeast strains for deuterated sitosterol that may be used in the development of next generation of mRNA vaccines.<sup>3</sup>

The yeast platform is also providing new deuterated lipids like squalene that will facilitate neutron research in new areas. Other lipids are in development originating from single cell marine protists, that produce a complex mix of triglycerides, saturated and polyunsaturated fatty acids, etc in order to survive in challenging environmental conditions. Complex purifications are required to achieve high purity compounds that can be isotopically labelled using heavy water or labelled substrates in the growth medium. These challenges are being taken on by the team of bio- and organic chemists to meet the growing demand from researchers in neutron scattering, and providing reagents and standards for mass spectrometry techniques.

### References

1. Strikingly Different Roles of SARS-CoV-2 Fusion Peptides Uncovered by Neutron Scattering <https://doi.org/10.1021/jacs.1c09856>
2. Apolipoprotein E Binding Drives Structural and Compositional Rearrangement of mRNA-Containing Lipid Nanoparticles <https://doi.org/10.1021/acsnano.0c10064>
3. Engineering of Phytosterol-Producing Yeast Platforms for Functional Reconstitution of Down-stream Biosynthetic Pathways <https://pubs.acs.org/doi/10.1021/acssynbio.0c00417>



69

## Update from the Australian Centre for Neutron Scattering

Jamie Schulz<sup>1</sup>

<sup>1</sup> ANSTO

**Corresponding Author(s):** [jamie.schulz@ansto.gov.au](mailto:jamie.schulz@ansto.gov.au)

The Australian Centre for Neutron Scattering (ACNS) utilises neutrons from Australia's multi-purpose research reactor, OPAL, to solve complex research and industrial problems for Australian and international users via merit-based access and user-pays programs. An update will be given on the OPAL reactor and its neutron beam facilities, the status of the neutron beam instruments and supporting capabilities, user program, and future plans.

47

## Cubosomes: A polytherapy based approach to combat antimicrobial resistance

hsin-hui shen<sup>1</sup>

<sup>1</sup> Monash

**Corresponding Author(s):** hsin-hui.shen@monash.edu

An imperative emerging problem in global healthcare is antimicrobial resistance. New antimicrobial therapeutics are urgently needed, including innovative nanotechnologies to fight multidrug-resistant bacterial superbugs. My team discovers (Lai et al. Nature Communications 2022) that a polytherapy based approach using lyotropic liquid crystalline nanoparticles (cubosomes) is far superior than loading the antibiotic within the lipid nanoparticles as is commonly done.

This work exploits a range of cross-disciplinary approaches, including the use of confocal microscopy and neutron reflectometry to mechanistically study the interactions between nanoparticles, antibiotics and bacterial membranes. Neutron reflectometry suggest the superior polytherapy activity was achieved via a two-step process. Firstly, electrostatic interactions between polymyxin and lipid A initially destabilize the outer lipid bilayer of the model membrane leaflet. Subsequently, influx of cubosomes into the bilayer result in significant further membrane disruption of the bilayer structure via a lipid exchange process. Our finding offers novel insight to the nanotherapeutics field whereby the 'one-size-fits-all' approach, i.e., focusing only on the conventional antibiotic-loaded nanoparticles, is not sufficient for the identification of optimal regimens with maximal bacterial killing.

22

## Investigating Allergenicity of Pollen Allergens in Thunderstorm Asthma Using Neutron Reflectometry

**Author(s):** Arslan Siddique<sup>1</sup>

**Co-author(s):** Janet Davies<sup>2</sup> ; Hui X. Ong<sup>3</sup> ; Daniella Traini<sup>3</sup> ; Patrick Spicer<sup>4</sup> ; Andrew Nelson<sup>5</sup> ; Stuart Prescott

<sup>6</sup>

<sup>1</sup> UNSW Sydney

<sup>2</sup> Queensland University of Technology (QUT)

<sup>3</sup> Woolcock Institute of Medical Research

<sup>4</sup> University of New South Wales (UNSW)

<sup>5</sup> ANSTO

<sup>6</sup> UNSW Chemical Engineering

**Corresponding Author(s):** a.siddique@unsw.edu.au

Epidemic thunderstorm asthma (ETSA) is a rare geographically dependent phenomenon that results in a dramatic outbreak of asthma attacks within a short span of time during seasonal thunderstorms. The high load of submicronic thunderstorm-borne aeroallergens proteins owing to their submicronic size can penetrate the narrow lower airways such as alveoli to trigger inhibition of adequate gaseous exchange during breathing. The inhalation of pollen allergens has been associated with the down-stream hypersensitive immune reactions, however, the underlying physicochemical mechanism of pollen allergen interactions with the lung surfactant monolayer and the epithelial bilayer of the alveoli is not well-understood.

In this talk, we demonstrate how a simplistic biomimetic model system can aid in the investigation of biointerfacial interactions such as allergen-lung surfactant (LS) monolayer and allergen-epithelial bilayer interactions. The LS monolayer and the bilayer was constituted of *dipalmitoylphosphatidyl-choline* (DPPC) and *phosphatidylcholine* (POPC), respectively. To mimic the atmospheric activity of thunderstorm, we generated the plasma activated water (PAW) containing reactive oxygen nitrogen species (RONS) for treating allergens. Our experimental data analysis revealed that model allergen protein, *Wisteria floribunda* Lectin (WFL) fetches RONS from the environment, ionizes strongly as well as form large aggregates in an aqueous solution. It was also observed that PAW-treated WFLs intensely adsorb on the hydrophobic LS monolayer and hydrophilic bilayer and undergo conformational alterations to maximize adsorption and cause insertion into the monolayer and bilayer, which

could contribute towards its enhanced allergenicity. The key findings of this study will enable effective diagnostics and therapeutics for the treatment of ETSA.

75

## Small Angle Neutron Scattering instrument Bilby: capabilities to study mainstream and complex systems

Anna Sokolova<sup>1</sup> ; Andrew Whitten<sup>1</sup> ; Liliana de Campo<sup>1</sup> ; Chun-Ming Wu<sup>2</sup>

<sup>1</sup> ANSTO

<sup>2</sup> NSRRC

**Corresponding Author(s):** anna.sokolova@ansto.gov.au, awh@ansto.gov.au, liliana.decampo@ansto.gov.au, cmw@ansto.gov.au

ANSTO for more than ten years successfully operates the Small Angle Neutron Scattering (SANS) instrument Quokka[1] and in 2016 commenced the user operation of the second SANS instrument, Bilby[2]. The Ultra-small angle scattering instrument Kookaburra[3] is completing the set of the SANS instruments at ANSTO.

Bilby exploits neutron Time-of-Flight (ToF) to extend the simultaneous measurable Q-range over and above what is possible on a conventional reactor-based monochromatic SANS instrument. In ToF mode, choppers are used to create neutron pulses comprising wavelengths between 2 and 20 Å of variable wavelength resolution (~3% – 30%). In addition, Bilby can operate in monochromatic mode using a velocity selector.

Two arrays of position sensitive detectors in combination with utilizing the wide wavelength range provide the capability to collect scattering data of a wide simultaneous angular range without changing the experimental set-up (maximum accessible Q on the instrument is 0.001-1.8Å<sup>-1</sup>).

Additionally, there is a range of sample environment available allowing to change sample conditions in situ, which is priceless for the study of a wide variety of samples ranging from colloids and hierarchical materials to metals. Here we present some recent examples.

### References

1. K. Wood et al, QUOKKA, the pinhole small-angle neutron scattering instrument at the OPAL Research Reactor, Australia: design, performance, operation and scientific highlights. *J. Appl. Crystallogr.* 51 (2018) 294-341.
2. A. Sokolova et al, Performance and characteristics of the BILBY time-of-flight small-angle neutron scattering instrument. *J. Appl. Crystallogr.* 52 (2019) 1-12.
3. C. Rehm et al, Design and performance of the variable-wavelength Bonse-Hart ultra-small-angle neutron scattering diffractometer KOOKABURRA at ANSTO. *J. Appl. Crystallogr.* 51 (2018) 1-8.

65

## Magnetic non-uniformity of antiferromagnetic FeRh film from polarized neutron reflectometry

**Author(s):** Sehwan Song<sup>1</sup> ; Sungkyun Park<sup>1</sup>

**Co-author(s):** Jiwoong Kim <sup>1</sup> ; Jisung Lee <sup>2</sup> ; Hyegyeong Kim <sup>1</sup> ; Noboru Miyata <sup>3</sup> ; Neeraj Kumar <sup>4</sup> ; Y. Soh <sup>4</sup> ; Jae Hyuck Jang <sup>2</sup> ; Chanyong Hwang <sup>5</sup> ; Brian Kirby <sup>6</sup>

<sup>1</sup> *Pusan National University*

<sup>2</sup> *Korea Basic Science Institute*

<sup>3</sup> *Compressive Research Organization for Science and Society*

<sup>4</sup> *Paul Scherrer Institute*

<sup>5</sup> *Korea Research Institute of Standards & Science*

<sup>6</sup> *National Institute Standard & Technology*

**Corresponding Author(s):** sehwan465@gmail.com

B2-phase FeRh exhibits a metamagnetic first-order phase transition from antiferromagnetic (AFM) to ferromagnetic (FM) around 370 K. It accompanies a volume expansion of about 1% and variation of electrical resistivity due to the increasing density-of-state at the Fermi level. Unlike bulk, unexpected FM characteristics have been observed in a thin-film form, even in the AFM state.

This presentation shows the detailed origin of the residual FM state by examining temperature-dependent physical properties. First, the residual ferromagnetic induces thermomagnetic irreversibility (e.g., spin-glass-like behavior) and negative magnetoresistance. Second, the non-uniform distribution of the magnetic profile at low temperature (i.e., below the transition temperature) is observed from the temperature-dependent polarized neutron reflectometry. Interestingly, the bottom and top interfaces exhibit an FM state, while the middle region is an AFM state. Furthermore, the bottom (top) interface shows a temperature-independent (-dependent) FM state, indicating that the FM origin of the interface between substrate and film (bottom interface) and capping layer (Al) and film (top interface) are due to structural distortion and non-stoichiometry respectively.

This work is supported in part by NRF-2020K1A3A7A09077715 and 2022M3H4A1A04085306.

10

## Phonon Engineering Thermoelectrics with Inelastic Neutron Scattering

**Author(s):** Caleb Stamper<sup>1</sup>

**Co-author(s):** Dehong Yu<sup>2</sup>; Kirrily Rule<sup>3</sup>; David Cortie<sup>4</sup>

<sup>1</sup> *University of Wollongong*

<sup>2</sup> *Australian Nuclear Science and Technology Organisation*

<sup>3</sup> *ANSTO*

<sup>4</sup> *The University of Wollongong*

**Corresponding Author(s):** cjs901@uowmail.edu.au

The challenge of designing a highly performing thermoelectric material lies in the requirement to de-couple the electronic and thermal transport; creating a material that has the electronic properties of a highly conducting crystal, while simultaneously having the thermal properties of a poorly conducting glass. The phonon-glass electron-crystal concept has contributed to significant research on the “phonon engineering” of materials. One exceptionally useful tool for aiding this engineering process is inelastic neutron scattering (INS). Information such as phonon linewidth, dispersion, and density of states (DOS), directly obtained by INS, can all be related back to the thermal properties of materials. In this talk, I will give an overview of the usefulness of INS as a tool to study phonons in thermoelectric materials by presenting some of our recent INS data on chalcogenide-based thermoelectric materials obtained at ACNS. In our work, we explore how INS can be used to understand the thermal conductivity of SnTe by studying the evolution of phonon modes as a function of temperature using Pelican (time-of-flight) and Sika (triple-axis). We also compare data obtained by each instrument and highlight significant and unexpected differences. Additionally, we study the phonon DOS of carbon nanomaterials, such as nanodiamond, to understand their intrinsic phonon lattice dynamics, and compare them with thermoelectrics to understand phonon scattering in nanocarbon doped thermoelectric composites due to thermal boundary resistance.

80

## McStas Simulations of Taipan

Liam Covey<sup>1</sup> ; Robert Stockton<sup>1</sup> ; Anton Stampfl<sup>2</sup>

<sup>1</sup> ANSTO

<sup>2</sup> Australian Nuclear Science and Technology Organisation

**Corresponding Author(s):** [aps@ansto.gov.au](mailto:aps@ansto.gov.au)

McStas is a well-known ray-tracing program for the design, development, investigation of neutron instruments as well as a potential learning and teaching tool for those that wish to understand or show how a neutron instrument works.

Here we build the thermal neutron triple-axis spectrometer on Taipan in McStas, configuring it to determine the resolution function in  $R(\omega, Q)$  under a number of conditioning states. We are initially

interested in how the lengths of the arms of the triple-axis alter the resolution function, in-particular how close we can place the analyser to the sample before losing resolution. We are wishing to potentially increase scattered flux without degrading resolution to the point of being unusable. We also wish to explore how reducing the thickness of the sapphire filter in the pre-optics affects the ultimate resolution of the spectrometer. We discuss our results to-date.

This study is the result of a Macquarie University PACE (Professional and Community Engagement) program where third/fourth year Physics students work for a number of weeks with a company or government institution on a research, development, or industry project.

79

## Taipan: The Thermal Triple-Axis and Be-Filter Spectrometers

Anton Stampfl<sup>1</sup> ; Kirrily Rule<sup>2</sup> ; Guochu Deng<sup>3</sup>

<sup>1</sup> *Australian Nuclear Science and Technology Organisation*

<sup>2</sup> *ANSTO*

<sup>3</sup> *Australian Nuclear Science and Technology Organization*

**Corresponding Author(s):** [aps@ansto.gov.au](mailto:aps@ansto.gov.au)

Two thermal spectrometers are available on Taipán, a single  $^3\text{He}$  detector triple axis spectrometer and a so-called Be-filter spectrometer that consists of an array of 30  $^3\text{He}$  detectors. The latter is predominately used to easily measure the vibrational density of states of powders while the former allows a wide range of measurements to be performed on single crystals, thin films, and powders, from phonon mapping, magnetic structure determination, and low energy excitation measurements. Both spectrometers are used to extract fundamental information about the magnetic and vibrational properties of a material under investigation.

Each spectrometer shares a common monochromator-set and pre-optics (virtual source, sapphire filters, and collimators). There are two monochromators available, a doubly focussed, PG(002) or Cu(002) monochromator, which gives access to incident neutron energies from ~5-200 meV and both of which may be separately driven into the neutron beam. When the triple-axis is in use, the Be-filter analyser spectrometer is hoisted out of the instrument dance floor and stored in an unoccupied space of the reactor beam-hall. While when the Be-filter analyser is in use the triple-axis analyser, detector, and sample stage is placed in the corner of the instrument dance-floor.

Here we describe the details of each spectrometer and report on some interesting recent studies.



30

## Rational Design of Advanced Nuclear Fuel Materials: New Pathways from In Situ Neutron Diffraction.

Jenny Stansby<sup>None</sup>; Yulia Mishchenko<sup>1</sup>; Sobhan Patnaik<sup>1</sup>; Vanessa Peterson<sup>2</sup>; Chris Baldwin<sup>2</sup>; Deborah Wakeham<sup>2</sup>  
; Patrick A Burr<sup>3</sup>; Denise Adorno-Lopes<sup>1</sup>; Edward Obbard<sup>3</sup>

<sup>1</sup> KTH

<sup>2</sup> ANSTO

<sup>3</sup> UNSW

**Corresponding Author(s):** [j.stansby@unsw.edu.au](mailto:j.stansby@unsw.edu.au)

Uranium nitride (UN) is a high-density nuclear fuel, under consideration as a drop-in replacement for existing light water reactor fuel assemblies. High uranium density fuels are desired because they allow increased fuel burnup for a given enrichment, meaning more energy can be extracted from the fuel before removal from the core. However, UN is known to corrode in steam i.e., conditions that would present during a loss of coolant accident. Doping with alloying compounds is known to affect the corrosion properties of UN, yet the rational design of advanced fuels requires an in-depth understanding of the corrosion mechanisms on the atomic scale.

Here, at the Australian Centre for Neutron Scattering, our team has developed sovereign capabilities for studying nuclear fuels under off-normal reactor conditions. Using UN-20vol%CrN and UN-20vol%ZrN as case studies, I will demonstrate how *in situ* neutron diffraction can provide real-time insight into when and how corrosion occurs under realistic accident-like conditions – results which cannot be obtained from conventional *ex situ* post-corrosion studies. The mechanistic insights gained lead to a new pathway for the design of advanced nuclear fuel materials with enhanced corrosion resistance in steam.

6

## Difference the Spot with Wombat

Andrew Studer<sup>1</sup>

<sup>1</sup> ACNS, ANSTO

**Corresponding Author(s):** [ajs@ansto.gov.au](mailto:ajs@ansto.gov.au)

Over the life of the Wombat diffractometer, there has been a steady interest in using the instrument for experiments on single crystals. With the implementation of the “Int3D” package (1) the capability now extends to full automated peak integration. This has already proven very useful; several examples will be reviewed.

1 Katcho *et.al.*, *Crystals* **2021**, *11*, 897

25

## Wombat – the high intensity diffractometer at OPAL

**Author(s):** Helen Maynard-Casely<sup>1</sup>

**Co-author(s):** Andrew Studer<sup>2</sup> ; Vanessa Peterson<sup>3</sup> ; Chin-Wei Wang<sup>4</sup> ; James Hester<sup>3</sup>

<sup>1</sup> *Australian Nuclear Science and Technology Organisation*

<sup>2</sup> *ACNS ANSTO*

<sup>3</sup> *ANSTO*

<sup>4</sup> *NSRRC*

**Corresponding Author(s):** [ajs@ansto.gov.au](mailto:ajs@ansto.gov.au)

Wombat is a high intensity neutron diffractometer located in the OPAL Neutron Guide Hall. It is primarily used as a high-speed powder diffractometer, but has also expanded into texture characterisation and single-crystal measurement, particularly diffuse scattering. The high performance comes from the combination of the best area detector ever constructed for neutron diffraction with the largest beam guide yet put into any research reactor and a correspondingly large crystal monochromator, all combine with the centre's polarisation capability to provide an instrument which is unique within the Southern hemisphere.

Wombat has been used to explore a broad range of materials, including: novel hydrogen-storage materials, negative-thermal-expansion materials, methane-ice clathrates, piezoelectrics, high performance battery anodes and cathodes, high strength alloys, multiferroics, superconductors and novel magnetic materials. Our poster will highlight both the capacity of the instrument, and some recent results.

37

## Investigation of the residual stress of steel after laser cleaning

Jiawei Tu<sup>1</sup> ; Anna Paradowska<sup>2</sup> ; Andrei Rode<sup>3</sup> ; Stephen Madden<sup>3</sup> ; Michael Drew<sup>4</sup> ; Ludovic Rapp<sup>3</sup> ; Meera Mohan<sup>5</sup> ; Gwénaëlle Proust<sup>6</sup>

<sup>1</sup> *School of Civil Engineering, The University of Sydney*

<sup>2</sup> *ANSTO*

<sup>3</sup> *Research School of Physics, Australian National University*

<sup>4</sup> *Australian Centre for Neutron Scattering, Australian Nuclear Science and Technology Organisation (ANSTO)*

<sup>5</sup> *Transport for NSW*

<sup>6</sup> *School of Civil Engineering, The University of Sydney; Sydney Manufacturing Hub, The University of Sydney*

**Corresponding Author(s):** [jitu3296@uni.sydney.edu.au](mailto:jitu3296@uni.sydney.edu.au)

**Key words:** residual stress, neutron diffraction, laser ablation, metal and alloys

Laser cleaning is a cutting-edge technique for the removal of contaminated and painted layers from solid surfaces by irradiating the surface with a laser beam. It is a non-contact process, which can be carefully controlled to minimize damage to the original substrate beneath a contaminated or corroded surface. The nanosecond or femtosecond laser treatment, in comparison to other cleaning techniques, significantly reduces the heat output to the structure, lowers the energy consumption, and optimises the control of the characteristics of the material surface, providing better long-term conservation of the steel structures such as the Sydney Harbour Bridge which is the focus of this project.

This research investigates residual stresses and mechanical properties of nanosecond and femtosecond laser-cleaned steels. Non-destructive X-ray and neutron diffraction residual stress measurements were performed with the team at the Australian Centre for Neutron Scattering and at Nuclear Fuel Cycle at ANSTO. X-ray diffraction was used for near-surface residual stress measurements. Neutron diffraction strain measurements on the Kowari instrument, were used to enable internal residual stress analysis.

The results of the residual stress measurements indicated that the femtosecond laser cleaning process has no detrimental effect on ablated steels. However, the nanosecond laser induces residual stresses in the substrate.

17

## Interrogation of the mechanism of Li-mediated ammonia electro-synthesis by in situ neutron reflectometry

Callum Weir-Lavelle<sup>None</sup> ; Rebecca Hodgetts<sup>1</sup> ; Hoang-Long Du<sup>1</sup> ; Andrew Nelson<sup>2</sup> ; Alexandr Simonov<sup>1</sup>

<sup>1</sup> Monash University

<sup>2</sup> ANSTO

**Corresponding Author(s):** callum.weir-lavelle@monash.edu

Ammonia has promising applications as a low-carbon fuel. However, its production via the Haber- Bosch process contributes 1.4% of all anthropogenic CO<sub>2</sub> emissions.<sup>1</sup> Alternatively, ammonia can be produced sustainably from N<sub>2</sub> and H<sub>2</sub>O directly using electro-synthesis powered by renewable energy.

The lithium-mediated nitrogen reduction reaction (Li-NRR) is the only known electrochemical process that can enable the conversion of N<sub>2</sub> to NH<sub>3</sub>.<sup>2</sup> The hypothesised Li-NRR mechanism includes the following steps:

$\text{Li}^+ + \text{e}^- \rightarrow \text{Li}^0$ ,  $6\text{Li}^0 + \text{N}_2 \rightarrow 2\text{Li}_3\text{N}$ , and  $\text{Li}_3\text{N} + 3\text{H}^+ \rightarrow \text{NH}_3 + 3\text{Li}^+$ .

However, the potential required to drive the lithium reduction induces other electrochemical transformations such as the unproductive reduction of protons to H<sub>2</sub> or hydrides, which decreases the faradaic efficiency. The solid electrolyte interface (SEI) is a thin layer of electrolyte degradation products which functionalise the electrode surface and is crucial to the Li-NRR effectiveness. Our ex situ X-ray photoelectron spectroscopic studies suggest that fluorides and sulphites are components of the SEI, but to elucidate its structure and formation whilst the surface is active, in situ characterisation is required.

At Monash, the current best-performing Li-NRR system has been recently developed<sup>3</sup> and improved to achieve near 100% faradaic efficiency and high performance at 1 bar N<sub>2</sub> pressure. These developments enabled preliminary in situ NR experiments and allowed the detection of initial SEI formation. These experiments provide a guide for our future work which will provide the first, unique insights into the mechanism of the Li-NRR.

84

## Sample Environment Developments from the Australian Centre For Neutron Scattering

**Author(s):** Rachel White<sup>1</sup>

**Co-author(s):** Timothy D'Adam<sup>2</sup>; Chris Baldwin<sup>1</sup>; Gene Davidson<sup>1</sup>; Amy Shumack<sup>1</sup>

<sup>1</sup> ANSTO

<sup>2</sup> ACNS, ANSTO

**Corresponding Author(s):** [rew@ansto.gov.au](mailto:rew@ansto.gov.au)

Sample environment at ACNS has had a productive period in 2021 and 2022. We received funding to replace equipment to maintain and improve our existing capabilities and undertaken development projects to create new capabilities.

We are currently commissioning a new Anton-Paar rheometer; Cobra+ cryostream; potentiostats and new cryofurnaces. Our funding has also allowed us to regain a capability we had in the past with the purchase of a Universal Testing Machine (UTM) for our diffraction and strain scanning neutron instruments. This project was conducted with close consultation with the user groups and

will be commissioned over the next year.

We have undertaken two significant design developments in the last 12 months. One is our own 4K-800K cryofurnace and the other is an induction furnace. The choice to create a cryofurnace is to offset some of the challenges we have faced with distance to suppliers and improve our future turn-around on repairs. The induction furnace will bring high temperature capability to the backscatter instrument, Emu, and the Be-filter used on the Taipan triple-axis spectrometer. It will also allow us greater flexibility for a growing demand with gas and vapour experiments at elevated temperatures. Both projects have been designed in-house and construction and commissioning will begin soon.

A Direct Laser Melting (DLM) deposition system, co-funded by a state grant, was designed and created by the team with assistance from other operations groups at ACNS. This system allows for in situ studies of residual stress during the additive manufacturing process and was recently commissioned on the strain scanner instrument, Kowari.

5

## Modelling Small-Angle Neutron Scattering of concentrated worm- like micelles

**Author(s):** Ashley Williams<sup>1</sup>

**Co-author(s):** Joshua King ; Anna Sokolova <sup>2</sup> ; Liliana de Campo <sup>3</sup> ; Rico Tabor <sup>4</sup>

<sup>1</sup> *PhD Student*

<sup>2</sup> *Dr*

<sup>3</sup> *ANSTO*

<sup>4</sup> *Monash University*

**Corresponding Author(s):** ashley.williams@monash.edu

Wormlike micelles are a self-assembly of surfactants that have solution state properties akin to polymers but are not covalently bound together, meaning the micelles can break and reform in a dynamic fashion. Industrially, wormlike micelles are utilised in personal care products such as shampoo and liquid soaps to provide viscosity (as well as to clean). The surfactant concentrations utilised in these formulations is usually greater than 10% by mass, whereby micelles are strongly interacting and entangling with one another. Small-angle neutron scattering is uniquely appropriate for in situ investigation of such soft colloidal materials, but for concentrated wormlike micelles, small-angle neutron scattering data is strongly dominated by a volume exclusion structure factor due to inter-micellar interactions. This describes the position of the micelles relative to each other due to the high concentration. Micellar shape and size (form factor) in such systems is typically modelled using a flexible cylinder model, but is only unambiguously obtained from dilute (non-interacting) systems that are far from the concentrations used in real products.

In standard analysis software, there is no option to reliably analyse these concentrated materials. We now have the ability to model this structure factor for polymers and wormlike micelles using the polymer reference interaction site model (PRISM), an extension of the flexible cylinder model. This model has been shown to reliably extract parameters for wormlike micelles such as those formed by the prototypical sodium laureth sulfate and cocamidopropyl betaine.

55

## Polycation radius of gyration in a polymeric ionic liquid (PIL): the PIL melt is not a theta solvent

**Author(s):** Lucas Wong<sup>1</sup>

**Co-author(s):** Seamus Jones<sup>2</sup>; Kathleen Wood<sup>3</sup>; Liliana de Campo<sup>4</sup>; Tamim Darwish<sup>4</sup>; Michael Moir<sup>4</sup>; Hua Li<sup>1</sup>; Rachel Segalman<sup>2</sup>; Gregory Warr<sup>5</sup>; Rob Atkin<sup>1</sup>

<sup>1</sup> *The University of Western Australia*

<sup>2</sup> *University of California, Santa Barbara*

<sup>3</sup> *Australian Nuclear Science and Technology Organisation*

<sup>4</sup> *ANSTO*

<sup>5</sup> *The University of Sydney*

**Corresponding Author(s):** lucas.wong@research.uwa.edu.au

Polymeric ionic liquids (PILs) are functionalised ionic liquids (ILs) that covalently attach one of the IL ions to a polymer backbone, with the other free ion acting as the counter ion. Due to their macromolecular architecture, PILs form viscous gels that are ionically conductive, making them ideal for use in solid-state electrochemical devices. The conformation of the polycation in the prototypical PIL poly(3-methyl-1-aminopropylimidazolylacrylamide) bis(trifluoromethylsulfonyl)imide (poly(3MAPIIm)TFSI) was probed using small-angle neutron scattering (SANS) and ultra-small-angle neutron scattering (USANS) at 25 °C and 80 °C. Poly(3MAPIIm)TFSI contains microvoids which lead to intense low q scattering that can be mitigated using mixtures of hydrogen- and deuterium-rich materials, allowing determination of the polycation conformation and radius of gyration ( $R_g$ ). In the pure PIL, the polycation adopts a random coil conformation with  $R_g = 52 \pm 0.5$  Å. In contrast to conventional polymer melts, the pure PIL is not a theta solvent for the polycation. The TFSI-anions, which comprise 48% v/v of the PIL, are strongly attracted to the polycation and act like small solvent molecules which leads to chain swelling analogous to an entangled, semi-dilute, or concentrated polymer solution in a good solvent.



56

## Quokka, the Monochromatic Small Angle Neutron Scattering instrument at ANSTO: Planned Upgrades & Scientific Highlights

Kathleen Wood<sup>1</sup> ; Jitendra Mata<sup>2</sup> ; Chun-Ming Wu<sup>3</sup> ; Elliot Gilbert<sup>2</sup> <sup>1</sup> *Australian Nuclear Science and Technology*

*Organisation*

<sup>2</sup> ANSTO

<sup>3</sup> NSRRC

**Corresponding Author(s):** kwo@ansto.gov.au

Quokka is a 40 m pinhole Small Angle Neutron Scattering instrument, operating with a neutron velocity selector, an adjustable collimation system providing source-sample distances of up to 20 m and a high-count rate 1 m<sup>2</sup> detector, capable of measuring neutrons over a flight path up to 20 m. Quokka routinely operates with focusing lens optics, capable of measuring down to a minimum Q value of  $6 \times 10^{-4} \text{ \AA}^{-1}$ . The instrument is also equipped with incident beam polarisation and analysis capability and features a unique detector capable of countrates in excess of 5 MHz.

Quokka is designed as a general-purpose SANS instrument, with a large sample area, capable of accommodating a variety of sample environments, suitable for in-situ studies in both hard and soft matter. Grazing incidence geometry is also available through a project funded by the Taiwanese National Synchrotron Radiation Research Center.

We present current planned upgrades, including replacement of our guide system, along with a selection of recent research highlights.

48

## GISANS to Study The Mechanism in Perforated Layers of Blend Films of a Symmetric Polystyrene-block-Poly(methyl methacrylate)

**Author(s):** Ya-Sen Sun<sup>1</sup> ; Chun-Ming Wu<sup>2</sup> ; Jia-Wen Hong<sup>None</sup>

**Co-author(s):** Yi-Qing Jian ; Yin-Ping Liao ; Hsiang-Ho Hung ; Tzu-Yen (Ian) Huang<sup>3</sup> ; Andrew Nelson<sup>4</sup>

<sup>1</sup> NCKU

<sup>2</sup> NSRRC

<sup>3</sup> Australian Centre for Neutron Scattering (ACNS) /Australian Nuclear Science and Technology Organisation (ANSTO)

<sup>4</sup> ANSTO

**Corresponding Author(s):** cmw@ansto.gov.au

The distributions of dPS in PLs // can be probed by grazing-incidence small-angle neutron scattering (GISANS) and time-of-flight neutron reflectivity (ToF-NR). In this study, by finely tuning the composition ( $\phi_{PS+dPS} = 63.8$  vol%) of the total PS/dPS component and annealing temperature (230 and 270

°C), P(S-b-MMA)/dPS blend films mainly form perforated layers with parallel orientation (hereafter PLs //). Where basically follow up our previous studied segmental distributions of polymer chains in blend films of a weakly-segregated polystyrene-block-poly(methyl methacrylate) [P(S-b-MMA)] and deuterated polystyrene (dPS). The GISANS and ToF-NR results offer evidence that dPS chains are preferentially located at the free surface and within the PS layers for blend films that were annealed at 230 °C. Upon annealing at 270 °C, dPS chains distribute within PS layers and perforated PMMA layers. Nevertheless, dPS chains still retain a surface preference for thin films. In contrast, such surface segregation of dPS chains is prohibited for thick films when annealed at 270 °C.

4

## Investigation of anomalous thermal and pressure-induced distortion in spin crossover materials

ZIXI XIE<sup>None</sup>**Corresponding Author(s):** zxie2054@uni.sydney.edu.au

Metal-organic framework (MOF) materials display sensitive responses to external stimuli, which are an emerging class of materials with functionality spanning many fields.<sup>1</sup> It remains a challenge to develop synthetic strategies for the rational design of MOFs that incorporate components with controllable properties. One approach to tuning the functionality of MOFs is to generate mixed-linker MOFs (MIXMOFs), where two or more ligands of similar structural geometry and solubility are incorporated into a single framework.<sup>2</sup> Herein, two Fe-based stimuli-responsive MOFs were generated and one of which consists of one ligand and another with mixed ligands. These two materials present reversible electronic state switching behaviour, known as spin crossover (SCO) phenomenon,<sup>3</sup> in the response to the change of temperature and pressure. Structural properties were characterised by using powder X-ray diffraction and neutron powder diffraction under pressure to demonstrate the correlations between lattice motions. Both materials display anomalous thermal-induced structural distortion showing scissor-type lattice flexing which is the colossal negative thermal expansion in one lattice direction and positive thermal expansion in another direction. Variable temperature magnetic susceptibility was conducted on these materials to demonstrate their SCO behaviours. The different extent of lattice motions and SCO behaviours under temperature and pressure of both materials was demonstrated and compared to reveal the ligand field and inter- or intramolecular effect on their properties.

[1] Nagarkar, S. S.; Desai, A. V.; Ghosh, S. K., *Chem. Asian. J.* 2014, 9, 2358-76.

[2] Kleist, W.; Jutz, F.; Maciejewski, M.; Baiker, A., *European Journal of Inorganic Chemistry* 2009, 2009 (24), 3552-3561.

[3] Gutlich, P.; Goodwin, H. A., Gutlich, P.; Goodwin, H. A., Eds. Springer Berlin Heidelberg, 2004; pp 1-47.

57

## The updates from the cold neutron axis spectrometer SIKA

Shinichiro Yano<sup>1</sup> ; Guochu Deng<sup>2</sup> ; Kirrily Rule<sup>3</sup> ; Nicolas de Souza<sup>4</sup> ; Andrew Manning<sup>3</sup> ; Jen-Chih Peng<sup>5</sup> ; Chun- Ming Wu<sup>1</sup>

<sup>1</sup> NSRRC

<sup>2</sup> Australian Nuclear Science and Technology Organization

<sup>3</sup> ANSTO

<sup>4</sup> ANSTO - Australian Centre for Neutron Scattering

<sup>5</sup> NISSRC

**Corresponding Author(s):** sin0928yano@gmail.com

We would like to give you updates about the cold-neutron triple-axis spectrometer SIKA that is on the CG4 beam port at the OPAL reactor, ACNS, ANSTO. We have reported the capabilities and status of SIKA in the last several user's meetings. In this meeting, we discuss the recent scientific achievements and technical developments of polarized neutron scattering experiments on SIKA focusing on the results from 2022.

35

## Vibrational Properties Beyond Debye Model

Dehong Yu<sup>1</sup><sup>1</sup> ANSTO**Corresponding Author(s):** dyu@ansto.gov.au

For over a century, the Debye model has served the fundamental law for our understanding of the vibrational properties of bulk solid materials which show a low energy relationship of  $g(\omega) \propto \omega^2$ , where  $\omega$  is the frequency and  $g(\omega)$  is the number of modes within an energy/frequency interval. However, recent discoveries show that under certain sceneries the Debye law failed. Upon the transition from solid to liquid phase, the low energy scaling changes to a linear relationship,  $g(\omega) \propto \omega$  [1]. Under 2D confinement, this relationship changes to an  $\omega^3$  behaviour for solid in both crystalline and amorphous phases [2].

[1] C. Stamper, D. Cortie, Z. Yue, X. L. Wang and D. H. Yu, *J. Phys. Chem. Lett.* 13, 3105 (2022) (editor's choice; front cover).

[2] Y. Yu, C. Yang, M. Baggioli, A. E. Philips, A. Zaccone, L. Zhang, R. Kajimoto, M. Nakamura, D H. Yu and L. Hong, *Nature Communications*, 13, 3649, (2022).

Acknowledgments: DHY would like to acknowledge all coauthors listed in the references on which the talk is based.

36

## Pressure Cells for Quasielastic and Inelastic Neutron Scatterings

Dehong Yu<sup>1</sup>; Richard Mole<sup>1</sup> <sup>1</sup> ANSTO

**Corresponding Author(s):** dyu@ansto.gov.au

Neutron diffraction under high pressure has become a routine technique to study material structure evolution versus pressure, however, it is still a challenging task to perform quasielastic (QENS) and inelastic neutron scattering (INS) under high pressure for material dynamics investigation. This is mainly attributed to the intrinsic several orders of magnitude lower cross section for the QENS and INS processes than elastic scattering. Consequently, a large amount of sample and minimum background contribution from the sample cell is essential for a successful high pressure QENS and INS. Two clamp pressure cells for QENS and INS have been developed. One is a hybrid CuBe/NiCrAl cell which is for relative high pressure up to 1.5 GPa and another one is made from high strength aluminium alloy (mesolite NA723) with pressure up to 0.5 GPa. The sample volume is 0.3 mL and 1 mL respectively. The pressure cells have been thoroughly calibrated and tested. In addition, the contribution to phonon density of states from the pressure cells and transmission medium has been evaluated. The applications of the pressure cells for INS and QENS is demonstrated by studies of pressure induced phase transition of plastic crystals.

63

## Structural characterization of niosome nanoparticle for ocular drug delivery

Yuhang Zhang<sup>None</sup> ; Rob Russell<sup>1</sup> ; Gurvinder Singh<sup>2</sup>

<sup>1</sup> ANSTO

<sup>2</sup> The school of biomedical engineering, the university of Sydney

**Corresponding Author(s):** yzha5601@uni.sydney.edu.au

Drug delivery to the posterior segment of the eye to treat wet-type Age-related Macular Degeneration (AMD) is challenging due to ocular barriers and low bioavailability of drug molecules. Nanoparticles hold great promise for treating posterior diseases (AMD) because of their good bioavailability, ability to deliver hydrophilic and hydrophobic drugs with a controlled and sustained release rate, enhanced residence time, and low administration frequency. Here, we demonstrate the formulation of drug loaded niosome based lipid nanoparticles from non-ionic surfactants and cholesterol molecules to treat AMD. Niosome nanoparticles have a bilayer structure and encapsulate the hydrophilic drug in the aqueous core. To improve the efficacy of the treatment, the formulation of niosome nanoparticle is optimised based on the size, surface potential, stability, drug loading and release profile. The result shows high drug loading efficiency (over 80%) of slightly negatively charged niosome nanoparticles of size 350 nm. To investigate the structural characteristics using small angle neutron scattering techniques, we formulated the niosome nanoparticles from deuterated cholesterol. The distribution of cholesterol within the bilayer and the membrane structural changes within the vitreous environment are investigated at different time interval, providing fundamental insights of niosome degradation and drug release profile. This knowledge is imperative to develop highly efficient therapeutic nanoparticles for sustained delivery of active biomolecules, such as antibody, RNA, and genes for treating ocular diseases.