

Polytron® P30B01 Polypropylene+LGF

Product Description:

Polytron P30B01 is Black, 30% Long Glass Fiber Reinforced, Heat Stabilized POLYPROPYLENE, The Glass Fibers are Chemically Coupled to the Polymer Matrix, The material is supplied in pellets that are typically 12mm in length. Fiber length is the length of the pellets. Typical applications include Structural Automotive Applications ,

For Under the Hood, Passengers' compartment parts Applications

Product Information:

Characteristic	Unit	Test method	Property value
Physical			
Density	g/cm ³	ISO 1183	1.12
Mold Shrinkage Flow 2mm	%	INTERNAL	0.1-0.2
Mold Shrinkage X Flow 2mm	%	INTERNAL	0.35-0.45
Mechanical			
Flexural Modulus	MPa	ISO 178	6700
Flexural Strength	MPa	ISO 178	155
Strain at Break	%	ISO 527-2/1A	2.2
Strain at Break 80C	%	ISO 527-2/1A	3.4
Tensile Modulus	MPa	ISO 527-2/1A	7000
Tensile Modulus 80C	MPa	ISO 527-2/1A	5400
Tensile Strength	MPa	ISO 527-2/1A	110
Tensile Strength 80C	MPa	ISO 527-2/1A	70
Impact			
Notched Charpy Impact @-40C Edgewise	kJ/m ²	ISO179-1/1eA	16
Notched Charpy Impact Edgewise	kJ/m ²	ISO179-1/1eA	18
Un Notched Charpy Impact @-40C Edgewise	kJ/m ²	ISO179-1/1eU	40
Un Notched Charpy Impact Edgewise	kJ/m ²	ISO179-1/1eU	50
Thermal			
HDT 0.45MPa	°C	ISO-75	158

Characteristic	Unit	Test method	Property value
HDT 1.8MPa	°C	ISO-75	155
Melting Point	°C	ISO 11357-3	168
Flammability			
Flammability FMVSS302	mm/min	FMVSS 302	0-100
Flammability HB 3mm		UL-94	HB

Regulations:

ROHS2: ROHS Compliance

SVHC: SVHC Compliance

Molding Guide:

Pre Drying Temperature: 80°C

Pre Drying Duration: 2-4 Hours

Processing recommendations:

Recommended Mold Temperature: 50-70°C

Feed: 220-240°C

Zone 1: 230-250°C

Zone 2: 230-250°C

Zone 3: 230-250°C

Revision #: 1

Revision Date: 21 Jul 2016

The technical data contained herein are guides to use Polyram resins. Information contained herein is to the best knowledge, true and assure. The customer is nevertheless obliged to run an incoming material control.