

**SALES SPECIFICATIONS**

Sales Specification No : 15792-16  
Effective Date : 04/30/2018  
Page No. 1 of 1

**EASTMAN****PRODUCT NAME****Eastman(TM) C-A-P Cellulose Ester NF (Pellets)****SPECIFICATIONS**

PROPERTY	LIMITS	TEST METHOD
NF Acetyl, %	21.5 - 26.0	TECE-A-NF-15792-POT-31
NF Phthalyl, %	30.0 - 36.0	TECE-A-NF-15792-POT-31
NF Free Acid, wt%	3.0 MAX	TECE-A-NF-15792-POT-31
NF Infrared Identity	PASS	TECE-A-NF-G-IR-5
NF Water, wt%	5.0 MAX	TECE-A-NF-15792-POT-31
NF Residue on Ignition, W%	0.1 MAX	TECE-A-NF-15792-GA-57
NF Viscosity, cps	45 - 90	TECE-A-NF-15792-V-32
NF Residual Solvents	PASS	TECE-A-NF-15792-POT-31

This methodology is derived from the United States Pharmacopeia (USP) National Formulary (NF), current edition

**ADDITIONAL INFORMATION** This specification describes Eastman C-A-P NF Powder or Pellets (Cellulose Ester). The Eastman C-A-P NF described in this specification is judged to be produced and handled in accordance with current Good Manufacturing Practices (cGMP) and meets each of the requirements listed in the section above according to the methods of testing Eastman C-A-P NF as set forth in the U.S Pharmacopoeia and National Formulary. Eastman C-A-P NF is available as a white pellet or as a white powder that may, on occasion, have some discolored particles present. These discolored particles, ranging from translucent off-white to black, are overheated Eastman C-A-P NF particles or low phthalyl substituted cellulose acetate occurring in the manufacturing process. These particles, when present, are in parts per million and are not preventable in our manufacturing process. They will either dissolve in the customer's solvent system dependent upon the solvent system) or can be removed by filtration of the customer's solution. This product is in compliance with the requirements in USP General Chapters 232 Elemental Impurities, ICH Q3D Guideline for Elemental Impurities and EP Metal Catalyst or Metal Reagent Residues.

Eastman Chemical Company · P.O. BOX 511 · Kingsport, Tennessee 37662 USA · 1-800-EASTMAN · 1-423-229-2000 · www.EASTMAN.com

Sales Specification available on Eastman.com

For reasons of safety and accuracy, the person performing this procedure must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers. Limits in this specification are applicable only to data obtained by the referenced test method.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale.